



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti		Hastelloy C		Aluminium alloy		PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM
						20	40	60	20	40	60									
See Sulphuric Acid 40 %																				
Acetaldehyde	CH <sub>3</sub> CHO	40			20	+	+	+	+	+	+	+	+	+	+	-	+	+	+	
Acetaldehyde	CH <sub>3</sub> CHO	40			40	+	+	+	o	+	+	+	+	+	-	+	+	+	+	
Acetaldehyde	CH <sub>3</sub> CHO	40			60	+	+	o	o	+	+	+	+	o	-	+	+	+	+	
Acetaldehyde	CH <sub>3</sub> CHO	TR	0,79	B	20	+	+	o	o	+	+	+	o	-	o	+	+	+	+	
Acetaldehyde	CH <sub>3</sub> CHO	TR			40	+	+	-	-	o	+	+	-	-	o	+	+	+	+	
Acetamide	CH <sub>3</sub> CO-NH <sub>2</sub>	TR	0,98		20	+	+	o	+	+	+	+	+	+	+	+	+	+	+	
Acetamide	CH <sub>3</sub> CO-NH <sub>2</sub>	TR			40	+	+	o	+	+	+	+	+	+	o	+	+	+	+	
Acetamide	CH <sub>3</sub> CO-NH <sub>2</sub>	TR			60	+	+	-	o	+	+	+	+	+	-	o	+	+	+	
Acetanhydride	(CH <sub>3</sub> CO) <sub>2</sub> O	TR	1,09	All	20	+	+	+	o	o	+	+	o	-	o	+	+	+	+	
Acetanhydride	(CH <sub>3</sub> CO) <sub>2</sub> O	TR			40	+	+	+	o	-	+	+	-	-	-	+	+	+	+	
Acetanhydride	(CH <sub>3</sub> CO) <sub>2</sub> O	TR			60	+	+	o	o	-	+	+	-	-	-	+	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	10			20	+	+	o	+	+	+	+	o	o	o	+	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	10			40	+	+	o	+	+	+	+	+	-	-	+	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	10			60	+	+	-	+	+	+	+	+	-	-	o	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	25			20	+	+	o	+	+	+	+	+	-	-	+	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	25			40	+	+	o	+	+	+	+	+	-	-	o	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	25			60	+	+	-	+	+	+	+	+	-	-	+	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	50			20	+	+	o	+	+	+	+	+	-	-	o	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	50			40	+	+	o	+	+	+	+	+	-	-	o	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	50			60	+	+	-	+	+	+	+	+	-	-	-	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	80			20	+	+	-	+	+	+	+	+	-	-	o	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	80			40	+	+	-	+	+	+	+	+	-	-	o	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	80			60	+	+	-	o	+	+	+	+	-	-	-	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	100	1,05		20	+	+	-	o	+	+	+	+	-	-	o	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	100			40	+	+	-	o	+	+	+	+	-	-	-	+	+	+	
Acetic Acid	CH <sub>3</sub> COOH	100			60	+	+	-	o	o	+	+	+	-	-	-	+	+	+	
Acetic Anhydride					See Acetanhydride															
Acetic Ether					See Ethyl Acetate															
Acetic Methyl Ester	CH <sub>3</sub> CO <sub>2</sub> CH <sub>3</sub>	100	0,93	AI	20	+	+	-	+	+	+	+	-	-	-	-	+	+	+	
Acetic Methyl Ester	CH <sub>3</sub> CO <sub>2</sub> CH <sub>3</sub>	100			40	+	+	-	+	o	+	+	+	-	-	-	+	+	+	
Acetic Methyl Ester	CH <sub>3</sub> CO <sub>2</sub> CH <sub>3</sub>	100			60	+	+	-	+	-	+	+	+	-	-	-	+	+	+	
Acetone	CH <sub>3</sub> CO-CH <sub>3</sub> +H <sub>2</sub> O	10		B	20	+	+	+	+	+	+	+	o	-	+	+	+	+	+	
Acetone	CH <sub>3</sub> CO-CH <sub>3</sub> +H <sub>2</sub> O	10			40	+	+	+	+	+	+	+	+	o	-	o	+	+	+	
Acetone	CH <sub>3</sub> CO-CH <sub>3</sub> +H <sub>2</sub> O	10			60	+	+	o	o	+	+	+	+	-	-	-	+	+	+	
Acetone	CH <sub>3</sub> CO-CH <sub>3</sub>	TR	0,79	B	20	+	+	+	+	o	+	+	+	-	-	+	+	+	+	
Acetone	CH <sub>3</sub> CO-CH <sub>3</sub>	TR			40	+	+	o	+	o	+	+	+	-	-	o	+	+	+	
Acetone	CH <sub>3</sub> CO-CH <sub>3</sub>	TR			60	+	+	o	o	-	+	+	+	-	-	-	+	+	+	
Acetonitrile	CH <sub>3</sub> -CN	TR	0,78	B	20	+	+	+	o	+	+	+	o	-	o	+	+	+	+	
Acetonitrile	CH <sub>3</sub> -CN	TR			40	+	+	+	+	-	+	+	o	-	-	-	+	+	+	
Acetonitrile	CH <sub>3</sub> -CN	TR			60	-	+	+	+	-	+	+	o	-	-	-	+	+	+	
Acetylene Dichloride					See Dichloroethylene 1,1															
Acrylonitrile	CH <sub>2</sub> =CH-CN	TR	0,81	AI	20	+	+	+	+	+	+	+	o	-	o	+	+	+	+	
Acrylonitrile	CH <sub>2</sub> =CH-CN	TR			40	+ <sup>1)</sup>	+	+	o	o	+	o	o	-	o	+	+	+	+	
Acrylonitrile	CH <sub>2</sub> =CH-CN	TR			60	+ <sup>1)</sup>	+	+	o	o	+	o	o	-	-	+	+	+	+	
Adipic Acid	C <sub>7</sub> H <sub>12</sub> O <sub>2</sub>	GL	0,89	All	20	+	+	o	+	+	+	+	+	+	+	+	+	+	+	

TR = technically pure, GL = saturated solution, H = commercial composition  
 + = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM	
Adipic Acid	C <sub>6</sub> H <sub>12</sub> O <sub>2</sub>	GL			40	+	-	+	+	+	+	+	+	+	+	+	
Adipic Acid	C <sub>6</sub> H <sub>12</sub> O <sub>2</sub>	GL			60	+	-	+	+	+	+	+	+	+	+	+	
Allyl Alcohol	H <sub>2</sub> C=CH-CH <sub>2</sub> -OH	96	0,87	B	20	+	o	+	+	+	+	o	+	o	+	+	
Allyl Alcohol	H <sub>2</sub> C=CH-CH <sub>2</sub> -OH	96			40	+	o	+	+	+	+	-	+	o	+	+	
Allyl Alcohol	H <sub>2</sub> C=CH-CH <sub>2</sub> -OH	96			60	+	o	+	+	+	+	-	+	o	+	+	
Alum					See Potassium Aluminium Sulphate												
Aluminium Chloride	AlCl <sub>3</sub>	10			20	o	+	-	+	+	+	+	+	+	+	+	+
Aluminium Chloride	AlCl <sub>3</sub>	10			40	o	+	-	+	+	+	+	+	+	+	+	+
Aluminium Chloride	AlCl <sub>3</sub>	10			60	o	+	-	+	+	+	+	+	o	+	+	+
Aluminium Chloride	AlCl <sub>3</sub>	GL	2,40		20	-	+	-	+	+	+	+	+	+	+	+	+
Aluminium Chloride	AlCl <sub>3</sub>	GL			40	-	+	-	+	+	+	+	+	+	+	+	+
Aluminium Chloride	AlCl <sub>3</sub>	GL			60	-	o	-	+	+	+	+	+	+	+	+	+
Aluminium Nitrate	Al(NO <sub>3</sub> ) <sub>3</sub>	GL			20	+	+	-	+	+	+	+	+	+	+	+	+
Aluminium Nitrate	Al(NO <sub>3</sub> ) <sub>3</sub>	GL			40	+	+	-	+	+	+	+	+	+	+	+	+
Aluminium Nitrate	Al(NO <sub>3</sub> ) <sub>3</sub>	GL			60	o	+	-	+ <sup>1)</sup>	+	+	-	+	o	+	+	+
Aluminium Sulphate	Al <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub>	10			20	+	+	-	+	+	+	+	+	+	+	+	+
Aluminium Sulphate	Al <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub>	10			40	+	+	-	+	+	+	+	+	+	+	+	+
Aluminium Sulphate	Al <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub>	10			60	+	+	-	+	+	+	+	+	+	+	+	+
Aluminium Sulphate	Al <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub>	GL	1,61		20	+	+	-	+	+	+	+	+	+	+	+	+
Aluminium Sulphate	Al <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub>	GL			40	o	+	-	+	+	+	+	+	+	+	+	+
Aluminium Sulphate	Al <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub>	GL			60	o	o	-	+	+	+	+	+	o	+	+	+
Amino Acid Amide					See Formamide												
Ammonia Solution					See Ammonia Water												
Ammonia Water	NH <sub>4</sub> ClOH	GL			20	+	+	+	+	+	+	+	-	+	+	+	+
Ammonia Water	NH <sub>4</sub> ClOH	GL			40	+	+	+	+	+	+	+	-	o	+	+	+
Ammonia Water	NH <sub>4</sub> ClOH	GL			60	+	+	+	+	+	+	+	-	o	+	+	+
Ammonium Acetate	CH <sub>3</sub> -COONH <sub>4</sub> Cl+H <sub>2</sub> O				20	+	+	+	+	+	+	+	+	+	+	+	+
Ammonium Acetate	CH <sub>3</sub> -COONH <sub>4</sub> Cl+H <sub>2</sub> O				40	+	+	o	+	+	+	+	+	+	+	+	+
Ammonium Acetate	CH <sub>3</sub> -COONH <sub>4</sub> Cl+H <sub>2</sub> O				60	+ <sup>1)</sup>	+	o	+ <sup>1)</sup>	+	+	o	+	+	+	+	+
Ammonium Bromide	NH <sub>4</sub> Br+H <sub>2</sub> O	40	1,27		20	o	+	-	+	+	+	+	+	+	+	+	+
Ammonium Bromide	NH <sub>4</sub> Br+H <sub>2</sub> O	40			40	o	+	-	+	+	+	+	+	+	+	+	+
Ammonium Bromide	NH <sub>4</sub> Br+H <sub>2</sub> O	40			60	-	o	-	+	+	+	+	+	+	+	+	+
Ammonium Carbonate	(NH <sub>4</sub> ) <sub>2</sub> CO <sub>3</sub> +H <sub>2</sub> O	25			20	+	+	+	+	+	+	+	+	+	+	+	+
Ammonium Carbonate	(NH <sub>4</sub> ) <sub>2</sub> CO <sub>3</sub> +H <sub>2</sub> O	25			40	+	+	+	+	+	+	+	+	+	+	+	+
Ammonium Carbonate	(NH <sub>4</sub> ) <sub>2</sub> CO <sub>3</sub> +H <sub>2</sub> O	25			60	+	+	+	+	+	+	+	+	+	+	+	+
Ammonium Chloride	NH <sub>4</sub> Cl+H <sub>2</sub> O	GL	1,07		20	+	+	-	+	+	+	+	+	+	+	+	+
Ammonium Chloride	NH <sub>4</sub> Cl+H <sub>2</sub> O	GL			40	+	+	-	+	+	+	+	+	+	+	+	+
Ammonium Chloride	NH <sub>4</sub> Cl+H <sub>2</sub> O	GL			60	o	+	-	+	+	+	+	+	+	+	+	+
Ammonium Fluoride	NH <sub>4</sub> F+H <sub>2</sub> O	14			20	o	+	-	+	+	+	+	+	+	+	+	+
Ammonium Fluoride	NH <sub>4</sub> F+H <sub>2</sub> O	14			40	o	+	-	+	+	+	+	+	+	+	+	+
Ammonium Fluoride	NH <sub>4</sub> F+H <sub>2</sub> O	14			60	-	+	-	+	+	+	+	+	o	+	+	+
Ammonium Fluosilicate	(NH <sub>4</sub> )SiF <sub>6</sub> +H <sub>2</sub> O	TR			20	+	+	-	+	+	+	+	+	+	+	+	+
Ammonium Hydrogen Fluoride	(NH <sub>4</sub> )HF <sub>2</sub>	50			20	o	o	-	+	+	+	+	+	-	+	+	+
Ammonium Hydrogen Fluoride	(NH <sub>4</sub> )HF <sub>2</sub>	50			40	-	o	-	+	+	+	+	o	-	-	+	+
Ammonium Hydrogen Fluoride	(NH <sub>4</sub> )HF <sub>2</sub>	50			60	-	o	-	+	+	+	+	o	-	-	+	+
Ammonium Monophosphate					See Ammonium Phosphate												
Ammonium Nitrate	NH <sub>4</sub> NO <sub>3</sub> +H <sub>2</sub> O	10			20	+	+	+	+	+	+	+	+	+	+	+	+
Ammonium Nitrate	NH <sub>4</sub> NO <sub>3</sub> +H <sub>2</sub> O	10			40	+	+	+	+	+	+	+	+	+	+	+	+
Ammonium Nitrate	NH <sub>4</sub> NO <sub>3</sub> +H <sub>2</sub> O	10			60	+	+	+	+	+	+	+	+	o	+	+	+

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM			
Ammonium Nitrate	$\text{NH}_4\text{NO}_3 + \text{H}_2\text{O}$	50	1,23		20	+	+	+	+	+	+	+	+	+	+	+	+			
Ammonium Nitrate	$\text{NH}_4\text{NO}_3 + \text{H}_2\text{O}$	50			40	+	+	+	+	+	+	+	+	+	+	+	+			
Ammonium Nitrate	$\text{NH}_4\text{NO}_3 + \text{H}_2\text{O}$	50			60	+	+	+	+	+	+	+	+	o	+	+	+			
Ammonium Nitrate	$\text{NH}_4\text{NO}_3 + \text{H}_2\text{O}$	GL			20	+	+	+	+	+	+	+	+	+	+	+	+			
Ammonium Nitrate	$\text{NH}_4\text{NO}_3 + \text{H}_2\text{O}$	GL			40	+	+	+	+	+	+	+	+	+	+	+	+			
Ammonium Nitrate	$\text{NH}_4\text{NO}_3 + \text{H}_2\text{O}$	GL			60	+	+	+	+	+	+	+	+	o	+	+	+			
Ammonium Oxalate	$(\text{COONH}_4)_2 + \text{H}_2\text{O}$	TR	1,50		20	+	+	+	+	+	+	+	+	+	+	+	+			
Ammonium Oxalate	$(\text{COONH}_4)_2 + \text{H}_2\text{O}$	TR			40	+	+	+	o	+	+	+	+	+	+	+	+			
Ammonium Oxalate	$(\text{COONH}_4)_2 + \text{H}_2\text{O}$	TR			60	+	+	+	o	+	+	+	+	+	o	+	+			
Ammonium Perchlorate	$\text{NH}_4\text{ClO}_4 + \text{H}_2\text{O}$	14	1,07		20	+	+	+	o	+	+	+	+	o	o	+	+			
Ammonium Perchlorate	$\text{NH}_4\text{ClO}_4 + \text{H}_2\text{O}$	14			40	o	+	o	o	+	+	+	+	-	o	+	+			
Ammonium Perchlorate	$\text{NH}_4\text{ClO}_4 + \text{H}_2\text{O}$	14			60	o	o	-	o	+	+	+	+	-	o	+	+			
Ammonium Phosphate	$\text{NH}_4\text{H}_2\text{PO}_4 + \text{H}_2\text{O}$	10			20	+	+	-	+	+	+	+	+	+	+	+	+			
Ammonium Phosphate	$\text{NH}_4\text{H}_2\text{PO}_4 + \text{H}_2\text{O}$	10			40	+	+	-	+	+	+	+	+	+	+	+	+			
Ammonium Phosphate	$\text{NH}_4\text{H}_2\text{PO}_4 + \text{H}_2\text{O}$	10			60	+	+	-	+	+	+	+	+	+	+	+	+			
Ammonium Sulphate	$(\text{NH}_4)_2\text{SO}_4 + \text{H}_2\text{O}$	10			20	+	+	+	+	+	+	+	+	+	+	+	+			
Ammonium Sulphate	$(\text{NH}_4)_2\text{SO}_4 + \text{H}_2\text{O}$	10			40	+	+	o	+	+	+	+	+	+	+	+	+			
Ammonium Sulphate	$(\text{NH}_4)_2\text{SO}_4 + \text{H}_2\text{O}$	10			60	+ <sup>1)</sup>	+	o	+ <sup>1)</sup>	+	+	o	+	o	+	+	+			
Ammonium Sulphate	$(\text{NH}_4)_2\text{SO}_4 + \text{H}_2\text{O}$	50	1,28		20	+	+	+	+	+	+	+	+	+	+	+	+			
Ammonium Sulphate	$(\text{NH}_4)_2\text{SO}_4 + \text{H}_2\text{O}$	50			40	+ <sup>1)</sup>	+	o	+ <sup>1)</sup>	+	+	o	+	+	+	+	+			
Ammonium Sulphate	$(\text{NH}_4)_2\text{SO}_4 + \text{H}_2\text{O}$	50			60	+ <sup>1)</sup>	+	o	+ <sup>1)</sup>	+	+	o	+	o	+	+	+			
Ammonium Sulphate	$(\text{NH}_4)_2\text{SO}_4 + \text{H}_2\text{O}$	GL	1,30		20	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	+	+	o	+	+	+	+	+			
Ammonium Sulphate	$(\text{NH}_4)_2\text{SO}_4 + \text{H}_2\text{O}$	GL			40	+ <sup>1)</sup>	+	o	+ <sup>1)</sup>	+	+	o	+	+	+	+	+			
Ammonium Sulphate	$(\text{NH}_4)_2\text{SO}_4 + \text{H}_2\text{O}$	GL			60	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	-	+	o	+	+	+			
Ammonium Sulphide	$\text{NH}_4\text{S} + \text{H}_2\text{O}$	10			20	+	+	-	+	+	+	+	+	+	+	+	+			
Ammonium Sulphide	$\text{NH}_4\text{S} + \text{H}_2\text{O}$	10			40	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	o	+	o	+	+	+			
Ammonium Sulphide	$\text{NH}_4\text{S} + \text{H}_2\text{O}$	10			60	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	o	+	o	+	+	+			
Amyl Acetate	$\text{CH}_3\text{-COOC}_5\text{H}_{11}$	TR	0,88	All	20	+	+	+	o	+	+	+	-	-	o	+	+			
Amyl Acetate	$\text{CH}_3\text{-COOC}_5\text{H}_{11}$	TR			40	+	+	+	-	o	+	+	-	-	-	+	+			
Amyl Acetate	$\text{CH}_3\text{-COOC}_5\text{H}_{11}$	TR			60	+ <sup>1)</sup>	+	+	-	o	+	o	-	-	-	+	+			
Amyl Alcohol	$\text{C}_5\text{H}_{11}\text{OH}$	TR	0,82	All	20	+	+	+	+	+	+	+	+	+	+	+	+			
Amyl Alcohol	$\text{C}_5\text{H}_{11}\text{OH}$	TR			40	+	+	o	+	+	+	+	+	o	+	+	+			
Amyl Alcohol	$\text{C}_5\text{H}_{11}\text{OH}$	TR			60	+	+	o	+	+	+	+	+	o	o	+	+			
Amyl Chloride	$\text{CH}_3(\text{CH}_2)_4\text{Cl}$	TR	0,87	AI	20	o	+	-	+	+	+	+	+	o	+	+	+			
Amyl Chloride	$\text{CH}_3(\text{CH}_2)_4\text{Cl}$	TR			40	-	+	-	o	+	+	+	+	o	+	+	+			
Amyl Chloride	$\text{CH}_3(\text{CH}_2)_4\text{Cl}$	TR			60	-	o	-	o	+	+	o	o	o	o	+	+			
Aniline	$\text{C}_6\text{H}_5\text{NH}_2$	TR	1,01	All	20	+	+	+	o	+	+	+	+	-	o	+	+			
Aniline	$\text{C}_6\text{H}_5\text{NH}_2$	TR			40	+	+	+	-	o	+	+	o	-	-	+	+			
Aniline	$\text{C}_6\text{H}_5\text{NH}_2$	TR			60	+ <sup>1)</sup>	+	+	-	o	+	o	-	-	+	+	+			
Anone						See Cyclohexanone														
Aqua Regia	$3\text{HCl} + \text{HNO}_3$				20	-	-	-	-	o	+	-	o	-	o	+	+			
Aqua Regia	$3\text{HCl} + \text{HNO}_3$				40	-	-	-	-	-	+	-	-	-	-	+	+			
Aqua Regia	$3\text{HCl} + \text{HNO}_3$				60	-	-	-	-	-	+	-	-	-	-	+	+			
Arsenic Acid	$\text{H}_3\text{ASO}_4$	10			20	+	+	-	+	+	+	+	+	+	+	+	+			
Arsenic Acid	$\text{H}_3\text{ASO}_4$	10			40	+	+	-	+	+	+	+	+	+	+	+	+			
Arsenic Acid	$\text{H}_3\text{ASO}_4$	10			60	+	+	-	+	+	+	+	+	+	+	+	+			
Arsenic Acid	$\text{H}_3\text{ASO}_4$	80			20	+	+	-	+	+	+	+	+	+	+	+	+			
Arsenic Acid	$\text{H}_3\text{ASO}_4$	80			40	+	+	-	+	+	+	+	+	+	+	+	+			
Arsenic Acid	$\text{H}_3\text{ASO}_4$	80			60	+	+	-	+	+	+	+	+	+	+	+	+			

TR = technically pure, GL = saturated solution, H = commercial composition  
 + = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM
Barium Chloride	BaCl <sub>2</sub>	10			20	-	+	o	+	+	+	+	+	+	+	+	+
Barium Chloride	BaCl <sub>2</sub>	10			40	-	+	o	+	+	+	+	+	+	+	+	+
Barium Chloride	BaCl <sub>2</sub>	25	1,27		20	o	+	o	+	+	+	+	+	+	+	+	+
Barium Chloride	BaCl <sub>2</sub>	25			40	o	+	o	+	+	+	+	+	+	+	+	+
Barium Hydroxide	Ba(OH) <sub>2</sub>	GL			20	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	o	+	+	+	+	+
Barium Hydroxide	Ba(OH) <sub>2</sub>	GL			40	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	o	+	+	+	+	+
Barium Hydroxide	Ba(OH) <sub>2</sub>	GL			60	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	o	+	o	+	+	+	+	+
Barium Sulphide	BaS	10			20	+	+	+	+	+	+	+	+	+	+	+	+
Benzaldehyde	C <sub>6</sub> H <sub>5</sub> CHO		1,05		20	+ <sup>1)</sup>	+	+	o	+	+	o	+	o	o	+	+
Benzaldehyde	C <sub>6</sub> H <sub>5</sub> CHO				40	+ <sup>1)</sup>	+	+	o	o	+	o	+	o	o	+	+
Benzaldehyde	C <sub>6</sub> H <sub>5</sub> CHO				60	+ <sup>1)</sup>	+	+	-	o	+	-	+	o	o	+	+
Benzaldehyde	C <sub>6</sub> H <sub>5</sub> CHO	30			20	+ <sup>1)</sup>	+	o	-	+	+	o	+	-	-	+	+
Benzaldehyde	C <sub>6</sub> H <sub>5</sub> CHO	TR	1,05	AllI	20	+	+	o	o	+	+	+	o	-	o	+	+
Benzene	C <sub>6</sub> H <sub>6</sub>	TR	0,88	AI	20	+	+	+	-	+	+	+	+	-	-	+	+
Benzoic Acid	C <sub>6</sub> H <sub>5</sub> COOH	10	1,27		20	+	+	+	+	+	+	+	+	-	-	+	+
Benzoic Acid	C <sub>6</sub> H <sub>5</sub> COOH	10			40	+	+	o	+	+	+	+	+	-	-	+	+
Benzoic Acid	C <sub>6</sub> H <sub>5</sub> COOH	10			60	+	+	o	o	+	+	+	+	-	-	+	+
Benzyl Alcohol	C <sub>6</sub> H <sub>5</sub> -CH <sub>2</sub> OH	TR	1,04		20	+	+	+	+	+	+	+	o	-	+	+	+
Benzyl Alcohol	C <sub>6</sub> H <sub>5</sub> -CH <sub>2</sub> OH	TR			40	+	+	+	+	+	+	+	o	-	o	+	+
Benzyl Alcohol	C <sub>6</sub> H <sub>5</sub> -CH <sub>2</sub> OH	TR			60	+	+	+	o	+	+	+	o	-	o	+	+
Benzyl Chloride	C <sub>6</sub> H <sub>5</sub> -CH <sub>2</sub> Cl		1,11	AllI	20	+	+	-	-	+	+	+	+	-	-	+	+
Benzyl Chloride	C <sub>6</sub> H <sub>5</sub> -CH <sub>2</sub> Cl				40	+	+	-	-	+	+	+	+	-	-	+	+
Benzyl Chloride	C <sub>6</sub> H <sub>5</sub> -CH <sub>2</sub> Cl				60	+	+	-	-	o	+	+	+	-	-	+	+
Bitter Almond Oil																	
Bitter Salt																	
Bleaching Solution																	
Blue Vitriol																	
Borax	Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> +10 H <sub>2</sub> O	10	1,03		20	+	+	-	+	+	+	+	+	+	+	+	+
Borax	Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> +10 H <sub>2</sub> O	10			40	+	+	-	+	+	+	+	+	+	+	+	+
Borax	Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> +10 H <sub>2</sub> O	10			60	+	+	-	+	+	+	+	+	+	+	+	+
Borax	Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> +10 H <sub>2</sub> O	GL			20	+	+	-	+	+	+	+	+	+	+	+	+
Borax	Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> +10 H <sub>2</sub> O	GL			40	+	+	-	+	+	+	+	+	+	+	+	+
Borax	Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> +10 H <sub>2</sub> O	GL			60	+	+	-	+	+	+	+	+	+	+	+	+
Boric Acid	H <sub>3</sub> BO <sub>3</sub> +H <sub>2</sub> O	10	1,01		20	+	+	+	+	+	+	+	+	+	+	+	+
Boric Acid	H <sub>3</sub> BO <sub>3</sub> +H <sub>2</sub> O	10			40	+	+	+	+	+	+	+	+	+	+	+	+
Boric Acid	H <sub>3</sub> BO <sub>3</sub> +H <sub>2</sub> O	10			60	+	+	+	+	+	+	+	+	+	+	+	+
Boric Acid	H <sub>3</sub> BO <sub>3</sub> +H <sub>2</sub> O	GL			20	+	+	-	+	+	+	+	+	+	+	+	+
Boric Acid	H <sub>3</sub> BO <sub>3</sub> +H <sub>2</sub> O	GL			40	+	+	-	+	+	+	+	+	+	+	+	+
Boric Acid	H <sub>3</sub> BO <sub>3</sub> +H <sub>2</sub> O	GL			60	+	+	-	+	+	+	+	+	+	+	+	+
Boron Trifluoride	BF <sub>3</sub> +H <sub>2</sub> O	10			20	o	o	-	+	+	+	+	+	+	+	+	+
Brake Fluid	Glycol Ether					+	+	+	+	+	+	+	+	-	+	+	+
Bromic Acid	HBrO <sub>3</sub>	10			20	o	+	-	+ <sup>1)</sup>	+	+	o	+	-	+	+	+
Bromic Acid	HBrO <sub>3</sub>	10			40	-	+	-	+ <sup>1)</sup>	+	+	o	+	-	+	+	+
Bromic Acid	HBrO <sub>3</sub>	10			60	-	+	-	o	+	+	o	+	-	o	+	+
Bromine	Br <sub>2</sub>	TR	3,19		20	-	+	-	-	+	+	-	o	-	-	+	+
Butane Carbonic Acid																	
Butane Diol	HO(CH <sub>2</sub> ) <sub>4</sub> OH	10			20	+	+	+	+	+	+	+	+	+	+	+	+
Butane Diol	HO(CH <sub>2</sub> ) <sub>4</sub> OH	10			40	+	+	+	+	+	+	+	+	+	+	+	+
Butane Diol	HO(CH <sub>2</sub> ) <sub>4</sub> OH	10			60	+	+	+	+	+	+	+	+	+	+	+	+
Butane Diol	HO(CH <sub>2</sub> ) <sub>4</sub> OH	TR			20	+	+	+	o	+	+	+	+	-	+	+	+

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %		Density [kg/dm³]	Danger class (VbF)	Temperature [C°]		Stainless Steel 316 Ti	Hasleloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM
Butane Diol	HO(CH <sub>2</sub> ) <sub>4</sub> OH	TR			40	+	+	o	o	+	+	+	+	-	+	+	+	+	
Butane Diol	HO(CH <sub>2</sub> ) <sub>4</sub> OH	TR			60	+	+	-	o	+	+	+	o	-	+	+	+	+	
Butane Triol	C <sub>4</sub> H <sub>10</sub> O <sub>3</sub>	TR			20	+	+	-	+	+	+	+	o	+	+	+	+	+	
Butanol	C <sub>4</sub> H <sub>9</sub> OH	TR	0,81	All	20	+	+	+	+	+	+	+	+	+	+	+	+	+	
Butanol	C <sub>4</sub> H <sub>9</sub> OH	TR			40	+	+	+	o	+	+	o	o	+	+	+	+	+	
Butanol	C <sub>4</sub> H <sub>9</sub> OH	TR			60	+	+	+	o	+	+	-	o	+	+	+	+	+	
Butanone (MEK)	C <sub>4</sub> H <sub>8</sub> O	TR	0,81	AI	20	+	+	-	+	-	+	o	-	-	+	+	+	+	
Butanone (MEK)	C <sub>4</sub> H <sub>8</sub> O	TR			40	+	+	-	o	-	+	-	-	-	o	+	+	+	
Butanone (MEK)	C <sub>4</sub> H <sub>8</sub> O	TR			60	+	+	-	o	-	+	-	-	-	o	+	+	+	
Butenal, trans-2-		See Propylene Aldehyde																	
Butyl Acetate	C <sub>6</sub> H <sub>12</sub> O <sub>2</sub>	TR	0,88	All	20	+ <sup>1)</sup>	+	+	o	+	+	+	o	-	+	+	+	+	
Butyl Acrylate	C <sub>5</sub> H <sub>8</sub> O <sub>2</sub>	TR		AI	20	+	+	o	-	o	+	+	-	-	o	+	+	+	
Butyl Alcohol		See Butanol																	
Butyl Chloride	C <sub>4</sub> H <sub>9</sub> Cl	TR	0,89	AI	20	o	+	-	+	+	+	+	-	-	-	+	+	+	
Butyl Chloride	C <sub>4</sub> H <sub>9</sub> Cl	TR			40	o	+	-	+ <sup>1)</sup>	+	+	o	-	-	-	+	+	+	
Butyl Chloride	C <sub>4</sub> H <sub>9</sub> Cl	TR			60	o	+	-	+ <sup>1)</sup>	+	+	o	-	-	-	+	+	+	
Butyl Ether		See Dibutyl Ether																	
Butyl Phenol	HOCH <sub>2</sub> CH <sub>2</sub> Cl(CH <sub>3</sub> ) <sub>3</sub>	TR			20	+	+	-	+	+	+	+	o	-	-	+	+	+	
Butyric Acid	C <sub>3</sub> H <sub>7</sub> COOH	20	0,88		20	+	+	+	-	+	+	+	+	-	+	+	+	+	
Butyric Acid	C <sub>3</sub> H <sub>7</sub> COOH	TR	0,96		20	+	+	+	-	+	+	+	o	-	o	+	+	+	
Calcium Bisulphite	Ca(HSO <sub>3</sub> ) <sub>2</sub>	10			20	+ <sup>1)</sup>	+	o	+ <sup>1)</sup>	+	+	o	+	-	+	+	+	+	
Calcium Bisulphite	Ca(HSO <sub>3</sub> ) <sub>2</sub>	GL			20	+ <sup>1)</sup>	+	o	+ <sup>1)</sup>	+	+	-	+	-	+	+	+	+	
Calcium Bisulphite	Ca(HSO <sub>3</sub> ) <sub>2</sub>	GL			40	+ <sup>1)</sup>	+	o	+ <sup>1)</sup>	+	+	-	+	-	+	+	+	+	
Calcium Bisulphite	Ca(HSO <sub>3</sub> ) <sub>2</sub>	GL			60	+ <sup>1)</sup>	+	o	+ <sup>1)</sup>	+	+	-	+	-	+	+	+	+	
Calcium Chlorate	CaClO <sub>3</sub> +H <sub>2</sub> O	10			20	+	+	o	+	+	+	+	+	+	+	+	+	+	
Calcium Chloride	CaCl <sub>2</sub> +H <sub>2</sub> O	10			20	+	+	+	+	+	+	+	+	+	+	+	+	+	
Calcium Chloride	CaCl <sub>2</sub> +H <sub>2</sub> O	10			40	+	+	+	+	+	+	+	+	+	+	+	+	+	
Calcium Chloride	CaCl <sub>2</sub> +H <sub>2</sub> O	10			60	o	o	+	+	+	+	+	+	+	+	+	+	+	
Calcium Chloride	CaCl <sub>2</sub> +H <sub>2</sub> O	GL	1,40		20	+	+	o	+	+	+	+	+	+	+	+	+	+	
Calcium Chloride	CaCl <sub>2</sub> +H <sub>2</sub> O	GL			40	+	+	o	+	+	+	+	+	+	+	+	+	+	
Calcium Chloride	CaCl <sub>2</sub> +H <sub>2</sub> O	GL			60	o	+	o	+	+	+	+	+	+	+	+	+	+	
Calcium Hydroxide	Ca(OH) <sub>2</sub>	15			20	+	+	-	+	+	+	+	+	+	+	+	+	+	
Calcium Hydroxide	Ca(OH) <sub>2</sub>	15			40	+	+	-	+	+	+	+	+	+	+	+	+	+	
Calcium Hydroxide	Ca(OH) <sub>2</sub>	15			60	+	+	-	+	+	+	+	+	o	+	+	+	+	
Calcium Hypochlorite	Ca(OCl) <sub>2</sub>	10			20	o	+	-	+ <sup>1)</sup>	+	+	o	+	+	+	+	+	+	
Calcium Hypochlorite	Ca(OCl) <sub>2</sub>	10			40	o	+	-	+ <sup>1)</sup>	+	+	o	+	o	+	+	+	+	
Calcium Hypochlorite	Ca(OCl) <sub>2</sub>	10			60	-	o	-	+ <sup>1)</sup>	+	+	o	+	-	+	+	+	+	
Calcium Nitrate	Ca(NO <sub>3</sub> ) <sub>2</sub>	50	1,48		20	+	+	+	+	+	+	+	+	+	+	+	+	+	
Calcium Nitrate	Ca(NO <sub>3</sub> ) <sub>2</sub>	50			40	+	+	+	+	+	+	+	+	+	+	+	+	+	
Camphor	C <sub>10</sub> H <sub>16</sub> O				20	+	+	+	+	+	+	+	o	+	o	+	+	+	
Camphor	C <sub>10</sub> H <sub>16</sub> O				40	+	+	+	+	+	+	+	o	o	o	o	o	+	
Camphor	C <sub>10</sub> H <sub>16</sub> O				60	+	+	+	+	+	+	+	o	o	o	o	o	+	
Caprylic Acid	CH <sub>3</sub> (CH <sub>2</sub> ) <sub>6</sub> COOH	0,92			20	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	o	+	-	+	+	+	+	
Caprylic Acid	CH <sub>3</sub> (CH <sub>2</sub> ) <sub>6</sub> COOH				40	+ <sup>1)</sup>	+	-	o	+	+	o	+	-	o	+	+	+	
Caprylic Acid	CH <sub>3</sub> (CH <sub>2</sub> ) <sub>6</sub> COOH				60	+ <sup>1)</sup>	+	-	-	+	+	o	o	-	-	+	+	+	
Carbamide		See Urea																	
Carboxlic Acid		See Phenol																	
Carbon Bisulphide	CS <sub>2</sub>	TR	1,27	AI	20	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	+	+	o	+	-	o	+	+	+	
Carbon Bisulphide	CS <sub>2</sub>	TR			40	+ <sup>1)</sup>	+	+	o	+	+	o	+	-	-	+	+	+	
Carbon Bisulphide	CS <sub>2</sub>	TR			60	+	+	+	o	+	+	-	+	-	-	+	+	+	

TR = technically pure, GL = saturated solution, H = commercial composition  
 + = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hasleloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM
Carbon Disulphide																	
Carbon Tetrachloride																	
Carbonic Acid																	
Caster Oil																	
Caustic Barya																	
Caustic Potash Solution																	
Caustic Soda																	
Cellosolve																	
Chloric Acid	HClO <sub>3</sub>	10			20	o	+	-	+ <sup>1)</sup>	+	+	-	+	-	+	+	+
Chloric Acid	HClO <sub>3</sub>	10			40	o	o	-	+ <sup>1)</sup>	+	+	-	+	-	+	+	+
Chloric Acid	HClO <sub>3</sub>	10			60	o	o	-	o	+	+	-	+	-	+	+	+
Chlorinated Diphenyl	C <sub>12</sub> H <sub>9</sub> Cl	TR			20	+ <sup>1)</sup>	+	+	-	+	+	o	+	-	-	+	+
Chlorine Bleaching																	
Chlorine Water	Cl <sub>2</sub> + H <sub>2</sub> O	GL			20	o	+	-	o	+	+	o	-	-	+	+	+
Chlorine Water	Cl <sub>2</sub> + H <sub>2</sub> O	GL			40	o	+	-	o	+	+	o	-	-	+	+	+
Chlorine Water	Cl <sub>2</sub> + H <sub>2</sub> O	GL			60	o	o	-	o	+	+	-	-	-	o	+	+
Chloroacetic Acid	C <sub>2</sub> H <sub>3</sub> ClO <sub>2</sub>	85	1,36		20	-	+	-	+ <sup>1)</sup>	+	+	o	+	-	+	+	+
Chloroacetic Acid	C <sub>2</sub> H <sub>3</sub> ClO <sub>2</sub>	85			40	-	o	-	+ <sup>1)</sup>	+	+	-	+	-	+	+	+
Chloroacetic Acid	C <sub>2</sub> H <sub>3</sub> ClO <sub>2</sub>	85			60	-	o	-	+ <sup>1)</sup>	+	+	-	+	-	+	+	+
Chloroacetic Acid	C <sub>2</sub> H <sub>3</sub> ClO <sub>2</sub>	98			20	-	+	-	+ <sup>1)</sup>	+	+	o	+	-	+	+	+
Chloroacetic Acid	C <sub>2</sub> H <sub>3</sub> ClO <sub>2</sub>	98			40	-	o	-	+ <sup>1)</sup>	+	+	-	+	-	+	+	+
Chloroacetic Acid	C <sub>2</sub> H <sub>3</sub> ClO <sub>2</sub>	98			60	-	o	-	+ <sup>1)</sup>	+	+	-	+	-	+	+	+
Chlorobenzene	C <sub>6</sub> H <sub>5</sub> Cl	TR	1,11	All	20	+	+	+	o	+	+	+	+	-	-	+	+
Chlorobenzene	C <sub>6</sub> H <sub>5</sub> Cl	TR			40	+	+	+	o	+	+	+	+	-	-	+	+
Chlorobenzene	C <sub>6</sub> H <sub>5</sub> Cl	TR			60	+	+	+	-	+	+	+	-	-	-	+	+
Chlorobutane																	
Chloroethane	C <sub>2</sub> H <sub>5</sub> Cl	TR	0,92		20	+	+	+	-	+	+	+	o	-	o	+	+
Chloroethanol	ClH <sub>2</sub> C-CH <sub>2</sub> OH	TR	1,20		20	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	o	-	+	o	+	+
Chloroethanol	ClH <sub>2</sub> C-CH <sub>2</sub> OH	TR			40	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	o	+	o	-	o	o	+	+
Chloroethanol	ClH <sub>2</sub> C-CH <sub>2</sub> OH	TR			60	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	o	+	o	-	-	o	+	+
Chloroethene																	
Chloroform	CHCl <sub>3</sub>	TR	1,48		20	+ <sup>1)</sup>	+	-	o	+	+	-	o	-	-	+	+
Chlorosulphonic Acid	HOSO <sub>2</sub> Cl	TR	1,77		20	+ <sup>1)</sup>	+	-	-	-	-	-	o	-	-	+	+
Chlorotoluene																	
Chromic Acid	CrO <sub>3</sub> +H <sub>2</sub> O	30			20	o	+	-	o	+	+	o	+	-	-	+	+
Chromic Acid	CrO <sub>3</sub> +H <sub>2</sub> O	50			20	o	o	-	-	+	+	o	+	-	-	+	+
Chromic Acid	CrO <sub>3</sub> +H <sub>2</sub> O	50			40	o	o	-	-	+	+	-	+	-	-	+	+
Chromic Acid	CrO <sub>3</sub> +H <sub>2</sub> O	50			60	o	o	-	-	+	+	-	+	-	-	+	+
Chromic-Sulphuric-Acid-Mixture	H <sub>2</sub> SO <sub>4</sub> +H <sub>2</sub> O+CrO <sub>3</sub>	50			20	o	o	-	o	+	+	-	+	-	-	+	+
Chromic-Sulphuric-Acid-Mixture	H <sub>2</sub> SO <sub>4</sub> +H <sub>2</sub> O+CrO <sub>3</sub>	50			40	o	o	-	-	+	+	-	+	-	-	+	+
Chromic-Sulphuric-Acid-Mixture	H <sub>2</sub> SO <sub>4</sub> +H <sub>2</sub> O+CrO <sub>3</sub>	50			60	o	o	-	-	+	+	-	+	-	-	+	+
Chromium Trioxide																	
Citric Acid	C <sub>6</sub> H <sub>8</sub> O <sub>7</sub>	50	1,22		20	+	+	-	+	+	+	+	+	+	+	+	+
Citric Acid	C <sub>6</sub> H <sub>8</sub> O <sub>7</sub>	50			40	o	+	-	+	+	+	+	+	+	+	+	+
Citric Acid	C <sub>6</sub> H <sub>8</sub> O <sub>7</sub>	50			60	o	+	-	+	+	+	+	+	+	+	+	+
Clophene																	
Clove Oil																	
Copper Acetate	(CH <sub>3</sub> CO <sub>2</sub> ) <sub>2</sub> Cu	50			20	+	+	-	+	+	+	+	+	+	+	+	+
Copper Acetate	(CH <sub>3</sub> CO <sub>2</sub> ) <sub>2</sub> Cu	50			40	+	+	-	+	+	+	+	+	+	+	+	+
Copper Acetate	(CH <sub>3</sub> CO <sub>2</sub> ) <sub>2</sub> Cu	50			60	+	+	-	+	+	+	+	+	+	o	+	+

TR = technically pure, GL = saturated solution, H = commercial composition  
 + = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM	
Copper Nitrate	Cu(NO <sub>3</sub> ) <sub>2</sub>	25	1,25		20	+	+	+	o	+	+	+	+	+	+	+	+	
Copper Nitrate	Cu(NO <sub>3</sub> ) <sub>2</sub>	25			40	+	+	+	o	+	+	+	+	+	+	+		
Copper Nitrate	Cu(NO <sub>3</sub> ) <sub>2</sub>	25			60	+	+	+	o	+	+	+	+	o	+	+	+	
Copper Sulphate	CuSO <sub>4</sub>	18	1,21		20	+	+	-	+	+	+	+	+	+	+	+	+	
Copper Sulphate	CuSO <sub>4</sub>	18			40	+	+	-	+	+	+	+	+	+	+	+	+	
Copper Sulphate	CuSO <sub>4</sub>	18			60	+	+	-	+	+	+	+	+	+	+	+	+	
Copper Sulphate	CuSO <sub>4</sub>	GL			20	+	+	-	o	+	+	+	+	+	+	+	+	
Copper Sulphate	CuSO <sub>4</sub>	GL			40	+	+	-	o	+	+	+	+	+	+	+	+	
Copper Sulphate	CuSO <sub>4</sub>	GL			60	+	+	-	o	+	+	+	+	o	+	+	+	
Corn Oil		TR			20	+	+	-	+	+	+	+	+	+	+	+	+	
Corn Oil		TR			40	+	+	-	+	+	+	+	+	+	o	+	+	
Corn Oil		TR			60	+	+	-	o	+	+	+	+	+	-	+	+	
Crotonaldehyde					See Propylenaldehyd													
Cupric Chloride	CuCl <sub>2</sub>	20	1,21		20	o	+	-	+	+	+	+	+	+	+	+	+	
Cupric Chloride	CuCl <sub>2</sub>	20			40	o	+	-	+	+	+	+	+	+	+	+	+	
Cupric Chloride	CuCl <sub>2</sub>	20			60	o	+	-	+	+	+	+	+	+	+	+	+	
Cuprous Chloride	CuCl	10			20	o	+	-	+	+	+	+	+	+	+	+	+	
Cuprous Chloride	CuCl	10			40	o	+	-	+	+	+	+	+	+	+	+	+	
Cuprous Chloride	CuCl	10			60	o	+	-	+	+	+	+	+	+	+	+	+	
Cyclohexane	C <sub>6</sub> H <sub>12</sub>	TR	0,78	AI	20	+	+	+	+	+	+	+	+	+	-	+	+	
Cyclohexane	C <sub>6</sub> H <sub>12</sub>	TR			40	+	+	+	+	+	+	+	+	+	-	+	+	
Cyclohexane	C <sub>6</sub> H <sub>12</sub>	TR			60	+	+	+	o	+	+	+	o	-	-	+	+	
Cyclohexanol	C <sub>6</sub> H <sub>12</sub> O	TR	0,94	All	20	+	+	-	+	+	+	+	o	o	o	+	+	
Cyclohexanol	C <sub>6</sub> H <sub>12</sub> O	TR			40	+	+	-	+	+	+	+	o	o	o	+	+	
Cyclohexanone	C <sub>6</sub> H <sub>10</sub> O	TR	0,95	All	20	+	+	+	+	+	+	+	-	-	o	+	+	
Decahydronaphthalin					See Decaline													
Decaline	C <sub>10</sub> H <sub>18</sub>	TR	0,88	All	20	+	+	+	o	+	+	+	+	o	-	+	+	
Decaline	C <sub>10</sub> H <sub>18</sub>	TR			40	+ <sup>1)</sup>	+	+	o	+	+	o	+	o	-	+	+	
Decaline	C <sub>10</sub> H <sub>18</sub>	TR			60	+ <sup>1)</sup>	+	+	o	+	+	o	+	o	-	+	+	
Dextrine	C <sub>6</sub> H <sub>10</sub> O <sub>5</sub> +H <sub>2</sub> O	18			20	+	+	+	+	+	+	+	+	+	+	+	+	
Dextrine	C <sub>6</sub> H <sub>10</sub> O <sub>5</sub> +H <sub>2</sub> O	18			40	+	+	+	+	+	+	+	+	o	+	+	+	
Dextrine	C <sub>6</sub> H <sub>10</sub> O <sub>5</sub> +H <sub>2</sub> O	18			60	+	+	+	+	+	+	+	+	o	+	+	+	
Dextrine	C <sub>6</sub> H <sub>10</sub> O <sub>5</sub> +H <sub>2</sub> O	GL			20	+	+	+	+	+	+	+	+	+	+	+	+	
Diacetone Alcohol	(CH <sub>3</sub> ) <sub>2</sub> C(OH)CH <sub>2</sub> COCH <sub>3</sub>	TR		B	20	+	+	-	-	+	+	+	+	-	+	+	+	
Diacetone Alcohol	(CH <sub>3</sub> ) <sub>2</sub> C(OH)CH <sub>2</sub> COCH <sub>3</sub>	TR			40	+	+	-	-	+	+	+	+	-	+	+	+	
Diacetone Alcohol	(CH <sub>3</sub> ) <sub>2</sub> C(OH)CH <sub>2</sub> COCH <sub>3</sub>	TR			60	+	+	-	-	+	+	+	+	-	+	+	+	
Diamide					See Hydrazine													
Dibromoethane					See Ethylene Bromide													
Dibutyl Ether	C <sub>8</sub> H <sub>18</sub> O	TR	0,77	All	20	+ <sup>1)</sup>	+	-	o	+	+	o	-	+	o	+	+	
Dibutyl Ether	C <sub>8</sub> H <sub>18</sub> O	TR			40	+ <sup>1)</sup>	+	-	+	+	+	-	-	o	o	+	+	
Dibutyl Ether	C <sub>8</sub> H <sub>18</sub> O	TR			60	+ <sup>1)</sup>	+	-	+	+	+	-	-	-	o	+	+	
Dibutyl Phthalate	C <sub>6</sub> H <sub>4</sub> (CO <sub>2</sub> C <sub>4</sub> H <sub>9</sub> ) <sub>2</sub>	TR	1,05		20	+	+	+	+	+	+	+	o	-	o	+	+	
Dibutyl Phthalate	C <sub>6</sub> H <sub>4</sub> (CO <sub>2</sub> C <sub>4</sub> H <sub>9</sub> ) <sub>2</sub>	TR			40	+ <sup>1)</sup>	+	+	o	+	+	+	-	-	+	+	+	
Dibutyl Phthalate	C <sub>6</sub> H <sub>4</sub> (CO <sub>2</sub> C <sub>4</sub> H <sub>9</sub> ) <sub>2</sub>	TR			60	+ <sup>1)</sup>	+	+	o	o	+	+	-	-	-	+	+	
Dibutyl Sebacate	C <sub>18</sub> H <sub>34</sub> O <sub>4</sub>	TR	0,94		20	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	o	o	-	-	+	+	
Dibutyl Sebacate	C <sub>18</sub> H <sub>34</sub> O <sub>4</sub>	TR			40	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	o	o	-	-	+	+	
Dibutyl Sebacate	C <sub>18</sub> H <sub>34</sub> O <sub>4</sub>	TR			60	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	o	o	-	-	+	+	
Dicaproic Acid					See Adipic Acid													
Dichloro Acetic Acid	CHCl <sub>2</sub> CO <sub>2</sub> H	TR	1,56		20	-	+	-	+ <sup>1)</sup>	+	+	-	o	-	+	+	+	
Dichloro Acetic Acid	CHCl <sub>2</sub> CO <sub>2</sub> H	TR			40	-	o	-	+ <sup>1)</sup>	+	+	-	o	-	+	+	+	

TR = technically pure, GL = saturated solution, H = commercial composition  
 + = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Alstalloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM
Dichloro Acetic Acid	CHCl <sub>2</sub> CO <sub>2</sub> H	TR			60	-	o	-	o	+	+	-	-	-	o	+	+
Dichlorodifluorine-Methane	CF <sub>2</sub> Cl <sub>2</sub>	TR	1,32		20	+	+	-	-	+	+ <sup>1)</sup>	+	o	o	o	o	+
Dichloroethane						See Chloroethane											
Dichloroethylene 1,1	C <sub>2</sub> H <sub>2</sub> Cl <sub>2</sub>	TR	1,22	AI	20	+ <sup>1)</sup>	+	-	o	+	+	-	+	-	+	-	+
Dichloroethylene 1,1	C <sub>2</sub> H <sub>2</sub> Cl <sub>2</sub>	TR			40	+ <sup>1)</sup>	+	-	o	+	+	-	+	+	-	+	+
Dichloroethylene 1,1	C <sub>2</sub> H <sub>2</sub> Cl <sub>2</sub>	TR			60	+ <sup>1)</sup>	+	-	o	+	+	-	+	+	-	+	+
Dichloromethane						See Methylene Chloride											
Diesel Fuel		H		All	20	+	+	+	o	+	+	+	+	+	-	+	+
Diesel Fuel		H			40	+	+	+	o	+	+	+	+	+	-	+	+
Diesel Fuel		H			60	+	+	+	-	+	+	+	+	+	-	+	+
Diethanolamine	HN(CH <sub>2</sub> CH <sub>2</sub> OH) <sub>2</sub>		1,10		20	+	+	-	+	o	+	+	o	-	+	+	+
Diethanolamine	HN(CH <sub>2</sub> CH <sub>2</sub> OH) <sub>2</sub>				40	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	o	+	o	o	-	+	+	+
Diethanolamine	HN(CH <sub>2</sub> CH <sub>2</sub> OH) <sub>2</sub>				60	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	-	+	o	o	-	+	+	+
Diethyl Ether						See Ether											
Diethylamine	C <sub>4</sub> H <sub>11</sub> N	10	0,70	B	20	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	o	+	-	-	-	+	+	+
Diethylcellosolve						See Ethyl Glycol											
Diethylene Oxide						See Tetrahydrofuran											
Diglycolic Acid	C <sub>4</sub> H <sub>6</sub> O <sub>6</sub>	30			20	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	+	-	+	o	+	+
Diglycolic Acid	C <sub>4</sub> H <sub>6</sub> O <sub>6</sub>	30			40	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	+	-	+	o	o	+
Diglycolic Acid	C <sub>4</sub> H <sub>6</sub> O <sub>6</sub>	30			60	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	+	-	+	o	o	+
Diglycolic Acid	C <sub>4</sub> H <sub>6</sub> O <sub>6</sub>	GL			20	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	+	-	+	o	+	+
Diisobutyl Ketone	C <sub>9</sub> H <sub>18</sub> O	TR			20	+	+	-	+	+	+	+	+	-	+	+	+
Diisobutyl Ketone	C <sub>9</sub> H <sub>18</sub> O	TR			40	+	+	-	+	+	+	+	+	-	+	+	+
Diisobutyl Ketone	C <sub>9</sub> H <sub>18</sub> O	TR			60	+	+	-	+	+	+	+	-	-	+	+	+
Diisopropyl Ether						See Isopropyl Ether											
Dimethyl Benzene						See Xylene											
Dimethyl Formamide (DMF)	C <sub>3</sub> H <sub>7</sub> NO	TR	0,95		20	+	+	-	+	-	+	+	-	o	+	+	+
Dimethyl Formamide (DMF)	C <sub>3</sub> H <sub>7</sub> NO	TR			40	+	+	-	+	-	+	+	-	-	+	+	+
Dimethyl Formamide (DMF)	C <sub>3</sub> H <sub>7</sub> NO	TR			60	+	+	-	+	-	+	+	-	-	+	+	+
Dimethyl Phthalate (DMP)	C <sub>6</sub> H <sub>4</sub> (COOCH <sub>3</sub> ) <sub>2</sub>	TR			20	+	+	-	+	+	+	+	-	-	-	+	+
Dimethyl Phthalate (DMP)	C <sub>6</sub> H <sub>4</sub> (COOCH <sub>3</sub> ) <sub>2</sub>	TR			40	+	+	-	+	+	+	+	-	-	-	+	+
Dimethyl Phthalate (DMP)	C <sub>6</sub> H <sub>4</sub> (COOCH <sub>3</sub> ) <sub>2</sub>	TR			60	+	+	-	+	+	+	+	-	-	-	+	+
Dimethylamine	(CH <sub>3</sub> ) <sub>2</sub> NH	TR	0,73		20	+	+	-	+	o	+	+	o	-	o	+	+
Dinonyl Phthalate	C <sub>26</sub> H <sub>42</sub> O <sub>4</sub>	TR			20	+	+	-	+	+	+	+	-	-	-	+	+
Dinonyl Phthalate	C <sub>26</sub> H <sub>42</sub> O <sub>4</sub>	TR			30	+	+	-	+	+	+	+	-	-	-	+	+
Diocyl Phthalate	C <sub>24</sub> H <sub>38</sub> O <sub>4</sub>	TR			20	+	+	-	o	+	+	+	+	-	-	+	+
Diocyl Phthalate	C <sub>24</sub> H <sub>38</sub> O <sub>4</sub>	TR			40	+	+	-	o	+	+	+	+	-	-	+	+
Diocyl Phthalate	C <sub>24</sub> H <sub>38</sub> O <sub>4</sub>	TR			60	+	+	-	o	o	+	+	+	-	-	+	+
Dioxane	C <sub>4</sub> H <sub>8</sub> O <sub>2</sub>	TR	1,03	B	20	+ <sup>1)</sup>	+	-	+	+	+	+	-	o	+	+	+
Dioxane	C <sub>4</sub> H <sub>8</sub> O <sub>2</sub>	TR			40	+	+	-	o	+	+	-	-	+	+	+	+
Dioxane	C <sub>4</sub> H <sub>8</sub> O <sub>2</sub>	TR			60	+ <sup>1)</sup>	+	-	-	-	+	o	-	-	+	+	+
DMF						See Dimethyl Formamide											
DMP						See Dimethyl Phthalate											
Eau de Javel						See Sodium Hypochlorite											
Epichlorhydine	H <sub>2</sub> C-O-CH-CH <sub>2</sub> Cl			All	20	o	+	-	+	+	+	+	-	-	-	+	+
Epichlorhydine	H <sub>2</sub> C-O-CH-CH <sub>2</sub> Cl				40	o	+	-	+	+	+	+	-	-	-	+	+
Epichlorhydine	H <sub>2</sub> C-O-CH-CH <sub>2</sub> Cl				60	o	+	-	+	+	+	+	-	-	-	+	+
Essential Oils						20	+	+	+	+	+	+	+	+	-	-	+
Essential Oils						40	+	+	+	+	+	+	+	o	-	-	+
Essential Oils						60	+	+	+	+	+	+	-	-	-	+	+

TR = technically pure, GL = saturated solution, H = commercial composition  
 + = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	RKM	NBR	EPDM	PTFE/FEP	FFKM
<b>Ethanal</b>																	
Ethane Dicarboxylic Acid	C <sub>4</sub> H <sub>6</sub> O <sub>4</sub>	50	1,06		20	+	+	-	+	+	+	+	+	+	+	+	+
Ethane Dicarboxylic Acid	C <sub>4</sub> H <sub>6</sub> O <sub>4</sub>	50			40	+	+	-	+	+	+	+	+	+	+	+	
Ethane Dicarboxylic Acid	C <sub>4</sub> H <sub>6</sub> O <sub>4</sub>	50			60	+	+	-	+	+	+	+	+	+	+	+	
Ethanol	CH <sub>3</sub> -CH <sub>2</sub> -OH	TR	0,79	B	20	+	+	+	+	+	+	+	+	+	+	+	+
Ethanol	CH <sub>3</sub> -CH <sub>2</sub> -OH	TR			40	+	+	+	+	+	+	+	o	+	+	+	
Ethanol	CH <sub>3</sub> -CH <sub>2</sub> -OH	TR			60	+	+	+	+	+	+	+	o	+	+	+	
Ether	(C <sub>2</sub> H <sub>5</sub> ) <sub>2</sub> O	TR	0,71	AI	20	+	+	+	-	+	+	+	o	o	o	+	+
Ethyl Acetate	H <sub>3</sub> C-COOC <sub>2</sub> H <sub>5</sub>	TR	0,90	AI	20	+	+	+	o	o	+	+	-	-	o	+	+
Ethyl Acetate	H <sub>3</sub> C-COOC <sub>2</sub> H <sub>5</sub>	TR			40	+	+	+	-	o	+	+	-	-	o	+	+
Ethyl Acetate	H <sub>3</sub> C-COOC <sub>2</sub> H <sub>5</sub>	TR			60	+	+	+	-	o	+	+	-	-	-	+	+
Ethyl Alcohol					See Ethanol												
Ethyl Benzene	C <sub>6</sub> H <sub>5</sub> -C <sub>2</sub> H <sub>5</sub>	TR	0,87	All	20	+ <sup>1)</sup>	+	+	o	+	+	-	o	-	-	+	+
Ethyl Benzene	C <sub>6</sub> H <sub>5</sub> -C <sub>2</sub> H <sub>5</sub>	TR			40	+ <sup>1)</sup>	+	+	-	+	+	-	-	-	-	+	+
Ethyl Benzene	C <sub>6</sub> H <sub>5</sub> -C <sub>2</sub> H <sub>5</sub>	TR			60	+ <sup>1)</sup>	+	+	-	+	+	-	-	-	-	+	+
Ethyl Chloracetate	ClH <sub>2</sub> C-CO-OC <sub>2</sub> H <sub>5</sub>			All	20	o	+	-	+	o	+	+	-	-	+	+	+
Ethyl Chloracetate	ClH <sub>2</sub> C-CO-OC <sub>2</sub> H <sub>5</sub>				40	o	+	-	+	o	+	+	-	-	+	+	+
Ethyl Chloracetate	ClH <sub>2</sub> C-CO-OC <sub>2</sub> H <sub>5</sub>				60	o	+	-	+	o	+	+	-	-	+	+	+
Ethyl Chloride					See Chloroethane												
Ethyl Dichloride	H <sub>3</sub> C-CHCl <sub>2</sub>		1,20	AI	20	+	+	+	o	+	+	+	+	o	o	o	+
Ethyl Dichloride	H <sub>3</sub> C-CHCl <sub>2</sub>				40	+	+	+	o	+	+	+	+	-	o	+	+
Ethyl Dichloride	H <sub>3</sub> C-CHCl <sub>2</sub>				60	+	+	+	-	+	+	+	o	-	-	+	+
Ethyl Ether					See Ether												
Ethyl Fluid					See Lead Tetraethyl												
Ethyl Glycol	C <sub>2</sub> H <sub>5</sub> -O-CH <sub>2</sub> -HC <sub>2</sub> OH	TR	0,93	All	20	+	+	-	-	+	+	+	+	+	-	+	+
Ethyl Glycol	C <sub>2</sub> H <sub>5</sub> -O-CH <sub>2</sub> -HC <sub>2</sub> OH	TR			40	+	+	-	-	+	+	+	+	-	+	+	+
Ethyl Glycol	C <sub>2</sub> H <sub>5</sub> -O-CH <sub>2</sub> -HC <sub>2</sub> OH	TR			60	+	+	-	-	+	+	+	+	-	+	+	+
Ethylene Bromide	CH <sub>2</sub> Br-CH <sub>2</sub> Br	TR	2,18		20	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	o	+	o	+	o	o	o	+
Ethylene Bromide	CH <sub>2</sub> Br-CH <sub>2</sub> Br	TR			40	+ <sup>1)</sup>	+	+	o	o	+	o	+	o	+	+	+
Ethylene Bromide	CH <sub>2</sub> Br-CH <sub>2</sub> Br	TR			60	+ <sup>1)</sup>	+	+	-	o	+	o	o	-	-	+	+
Ethylene Chlorhydrine					See Chloroethanol												
Ethylene Diamine	H <sub>2</sub> N-CH <sub>2</sub> -CH <sub>2</sub> -NH <sub>2</sub>	TR	0,98		20	+	+	+	+	+	+	+	o	o	o	+	+
Ethylene Diamine	H <sub>2</sub> N-CH <sub>2</sub> -CH <sub>2</sub> -NH <sub>2</sub>	TR			40	+	+	+	+	+	+	+	o	o	o	+	+
Ethylene Diamine	H <sub>2</sub> N-CH <sub>2</sub> -CH <sub>2</sub> -NH <sub>2</sub>	TR			60	+	+	+	+	+	+	+	-	+	+	+	+
Ethylene Dicarboxylic Acid					See Maleic Acid												
Ethylene Glycol	C <sub>2</sub> H <sub>6</sub> O <sub>2</sub>	TR	1,11		20	+	+	+	+	+	+	+	+	+	+	+	+
Ethylene Glycol	C <sub>2</sub> H <sub>6</sub> O <sub>2</sub>	TR			40	+	+	+	+	+	+	+	+	+	+	+	+
Ethylene Glycol	C <sub>2</sub> H <sub>6</sub> O <sub>2</sub>	TR			60	+	+	+	+	+	+	+	+	+	+	+	+
Fatty Acids	C <sub>17</sub> H <sub>33</sub> CO <sub>2</sub> H	100	0,90		20	+	+	-	o	+	+	+	+	o	-	+	+
Fatty Acids	C <sub>17</sub> H <sub>33</sub> CO <sub>2</sub> H	100			40	+	+	-	o	+	+	+	+	-	-	+	+
Fatty Acids	C <sub>17</sub> H <sub>33</sub> CO <sub>2</sub> H	100			60	+	+	-	o	+	+	+	+	-	-	+	+
Ferric Sulphate	Fe <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub>	50	1,61		20	+	+	-	+	+	+	+	+	+	+	+	+
Ferric Sulphate	Fe <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub>	50			40	+	+	-	+	+	+	+	+	+	+	+	+
Ferric Sulphate	Fe <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub>	50			60	+	+	-	+	+	+	+	+	+	+	+	+
Ferrichloride	FeCl <sub>3</sub> +H <sub>2</sub> O	50	1,55		20	-	+	-	+	+	+	+	+	+	+	+	+
Ferrichloride	FeCl <sub>3</sub> +H <sub>2</sub> O	50			40	-	o	-	+	+	+	+	+	+	+	+	+
Ferrichloride	FeCl <sub>3</sub> +H <sub>2</sub> O	50			60	-	-	-	+	+	+	+	+	+	+	+	+
Ferro					See Ferrous Nitrate												
Ferrochloride	FeCl <sub>2</sub> +H <sub>2</sub> O	10	1,09		20	+	+	-	+	+	+	+	+	+	+	+	+
Ferrochloride	FeCl <sub>2</sub> +H <sub>2</sub> O	10			40	o	+	-	+	+	+	+	+	+	+	+	+

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FFEP	FFKM	
Ferrochloride	FeCl <sub>2</sub> +H <sub>2</sub> O	10			60	o o - + + + + + + + + + + + +											
Ferrochloride	FeCl <sub>2</sub> +H <sub>2</sub> O	50			20	+ + - + + + + + + + + + + + +											
Ferrochloride	FeCl <sub>2</sub> +H <sub>2</sub> O	50			40	o + - + + + + + + + + + + + +											
Ferrochloride	FeCl <sub>2</sub> +H <sub>2</sub> O	50			60	o + - + + + + + + + + + + + +											
Ferrocyanide of Potassium																	
Ferro-Gallic-Inc																	
Ferrosulphate	FeSO <sub>4</sub>	20	1,21		20	+ <sup>1)</sup> + + + + + + + + + + + + + +											
Ferrosulphate	FeSO <sub>4</sub>	20			40	+ <sup>1)</sup> + + + + + + + + + + + + + +											
Ferrosulphate	FeSO <sub>4</sub>	20			60	+ <sup>1)</sup> + + + + + + + + + + + + + +											
Ferrous Nitrate	Fe(NO <sub>3</sub> ) <sub>2</sub>	TR			20	+ + - + + + + + + + + + + + +											
Ferrous Nitrate	Fe(NO <sub>3</sub> ) <sub>2</sub>	TR			40	+ + - + + + + + + + + + + + +											
Ferrous Nitrate	Fe(NO <sub>3</sub> ) <sub>2</sub>	TR			60	+ + - + + + + + + + + + + + +											
Finger Nail Polish Remover																	
Flourammon																	
Formaldehyde	CH <sub>2</sub> O+H <sub>2</sub> O	10			20	+ + - + + + + + + + + + + + +											
Formaldehyde	CH <sub>2</sub> O+H <sub>2</sub> O	10			40	+ + - + + + + + + + + + + + +											
Formaldehyde	CH <sub>2</sub> O+H <sub>2</sub> O	10			60	+ + - + + + + + + + + + + + +											
Formaldehyde	CH <sub>2</sub> O+H <sub>2</sub> O	35	1,10	All	20	+ + - + + + + + + + + + + +											
Formaldehyde	CH <sub>2</sub> O+H <sub>2</sub> O	40		All	20	+ + - + + + + + + + + + + +											
Formalin																	
Formamide	HCONH <sub>2</sub>	100			20	+ + + + + + + + + + + + + +											
Formamide	HCONH <sub>2</sub>	100			40	+ + + + + + + + + + + + + +											
Formamide	HCONH <sub>2</sub>	100			60	+ + + + + + + + + + + + + +											
Formic Acid	HCOOH	50			20	+ + - + + + + + + + + + +											
Formic Acid	HCOOH	50			40	+ + - o + + + + + + + +											
Formic Acid	HCOOH	50			60	o + - + + + + + + + + + +											
Formic Acid	HCOOH	85	1,22	All	20	+ + - + + + + + + + + + +											
Formic Acid	HCOOH	85		All	40	o + - o + + + + + + + +											
Formic Acid	HCOOH	85		All	60	o + - - + + + + + + + +											
Freon 12																	
Fruit Juice		H			20	+ + o + + + + + + + + + +											
Fruit Juice		H			40	+ + o + + + + + + + + + +											
Fruit Juice		H			60	+ + o + + + + + + + + + +											
Fuel Oil		H		All	20	+ + + + + + + + + + + + + +											
Fuel Oil		H			40	+ + + o + + + + + + + + +											
Fuel Oil		H			60	+ + + o + + + + + + + + +											
Furfuryl Alcohol	C <sub>5</sub> H <sub>8</sub> O <sub>2</sub>	TR	1,13	All	20	+ + + + + + + + + + + + +											
Furfuryl Alcohol	C <sub>5</sub> H <sub>8</sub> O <sub>2</sub>	TR			40	+ + + o + + + + + + + + +											
Furfuryl Alcohol	C <sub>5</sub> H <sub>8</sub> O <sub>2</sub>	TR			60	+ + + o o + + + + + + + +											
Gallic Acid	C <sub>6</sub> H <sub>2</sub> (OH) <sub>3</sub> CO <sub>2</sub> H	50			20	+ <sup>1)</sup> + - + <sup>1)</sup> + + + + + + + +											
Gallotannic Acid																	
Glacial Acetic Acid																	
Glauber's Salt																	
Gluconic Acid	C <sub>6</sub> H <sub>12</sub> O <sub>7</sub>				20	+ + - + + + + + + + + + +											
Gluconic Acid	C <sub>6</sub> H <sub>12</sub> O <sub>7</sub>				40	+ + - + + + + + + + + + +											
Gluconic Acid	C <sub>6</sub> H <sub>12</sub> O <sub>7</sub>				60	+ + - + + + + + + + + + +											
Glucose																	
Glucose Solution	C <sub>6</sub> H <sub>12</sub> O <sub>6</sub>	GL	1,13		20	+ + + + + + + + + + + + +											
Glucose Solution	C <sub>6</sub> H <sub>12</sub> O <sub>6</sub>	GL			40	+ + + + + + + + + + + + +											
Glucose Solution	C <sub>6</sub> H <sub>12</sub> O <sub>6</sub>	GL			60	+ + + + + + + + + + + + +											

TR = technically pure, GL = saturated solution, H = commercial composition  
 + = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hasleloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM		
Glycerine	C <sub>3</sub> H <sub>8</sub> O <sub>3</sub>	TR	1,26		20	+	+	+	+	+	+	+	+	o	+	+	+		
Glycerine	C <sub>3</sub> H <sub>8</sub> O <sub>3</sub>	TR			40	+	+	+	+	+	+	+	+	o	+	+	+		
Glycerine	C <sub>3</sub> H <sub>8</sub> O <sub>3</sub>	TR			60	+	+	+	+	+	+	+	+	o	+	+	+		
Glycol					See Ethylene Glycol														
Glycolic Acid	C <sub>2</sub> H <sub>4</sub> O <sub>3</sub>	37			20	+	+	-	+	+	+	+	+	+	+	+	+		
Glycolic Acid	C <sub>2</sub> H <sub>4</sub> O <sub>3</sub>	70			20	+	+	-	+	+	+	+	+	-	+	+	+		
Glycolic Acid	C <sub>2</sub> H <sub>4</sub> O <sub>3</sub>	70			40	+	+	-	o	o	+	+	o	-	o	+	+		
Glycolic Acid	C <sub>2</sub> H <sub>4</sub> O <sub>3</sub>	70			60	+	+	-	-	o	+	+	o	-	-	+	+		
Glycose					See Glycerine														
Heptane	C <sub>7</sub> H <sub>16</sub>	TR	0,68	AI	20	+	+	+	+	+	+	+	+	+	-	+	+		
Heptane	C <sub>7</sub> H <sub>16</sub>	TR			40	+	+	+	+	+	+	+	+	+	-	+	+		
Heptane	C <sub>7</sub> H <sub>16</sub>	TR			60	+	+	+	o	+	+	+	+	+	-	+	+		
Hexahydrobenzene					See Cyclohexane														
Hexalin					See Cyclohexanol														
Hexamethylenetetramine	(CH <sub>2</sub> ) <sub>6</sub> N <sub>4</sub>	10			20	+	+	+	-	+	+	+	o	-	-	+	+		
Hexamethylenetetramine	(CH <sub>2</sub> ) <sub>6</sub> N <sub>4</sub>	10			40	+	+	+	-	+	+	+	-	-	-	+	+		
Hexamethylenetetramine	(CH <sub>2</sub> ) <sub>6</sub> N <sub>4</sub>	10			60	+	+	+	-	o	+	+	-	-	-	+	+		
Hexamine					See Hexamethylenetetramine														
Hexane	C <sub>6</sub> H <sub>14</sub>	TR		AI	20	+	+	+	+	+	+	+	+	+	-	+	+		
Hexane	C <sub>6</sub> H <sub>14</sub>	TR			40	+	+	+	+	+	+	+	+	+	-	+	+		
Hexane	C <sub>6</sub> H <sub>14</sub>	TR			60	+	+	+	o	+	+	+	+	-	+	+			
Hexanedioc Acid					See Adipic Acid														
Hexanol	C <sub>6</sub> H <sub>13</sub> OH		0,82	AllI	20	+	+	-	+	+	+	+	+	-	+	+	+		
Hexylalcohol					See Hexanol														
Hydrazine	H <sub>2</sub> N-NH <sub>2</sub>	TR	1,08	B	20	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	+	-	+	+	+	+	+	
Hydrazine	H <sub>2</sub> N-NH <sub>2</sub>	TR			40	o	+	-	o	+	+	+	-	+	o	o	+	+	
Hydrazine	H <sub>2</sub> N-NH <sub>2</sub>	TR			60	-	o	-	-	+	+	-	o	-	-	+	+		
Hydriodic Acid	HJ	TR			20	o	o	-	+ <sup>1)</sup>	+	+	+	-	+	+	+	+		
Hydriodic Acid	HJ	TR			40	o	o	-	+ <sup>1)</sup>	+	+	+	-	+	o	+	+		
Hydriodic Acid	HJ	TR			60	-	o	-	+ <sup>1)</sup>	+	+	+	-	+	o	+	+		
Hydrobromic Acid	HBr + H <sub>2</sub> O	10	1,07		20	-	o	-	+ <sup>1)</sup>	+	+	o	+	-	+	+	+		
Hydrobromic Acid	HBr + H <sub>2</sub> O	10			40	-	o	-	+ <sup>1)</sup>	+	+	o	+	-	+	+	+		
Hydrobromic Acid	HBr + H <sub>2</sub> O	10			60	-	-	-	+ <sup>1)</sup>	+	+	o	+	-	o	+	+		
Hydrobromic Acid	HBr + H <sub>2</sub> O	48	1,44		20	-	o	-	+ <sup>1)</sup>	+	+	o	+	o	+	+	+		
Hydrobromic Acid	HBr + H <sub>2</sub> O	48			40	-	o	-	+ <sup>1)</sup>	+	+	o	+	-	+	+	+		
Hydrobromic Acid	HBr + H <sub>2</sub> O	48			60	-	-	-	+ <sup>1)</sup>	+	+	o	+	-	o	+	+		
Hydrochloric Acid	HCl	10	1,05		20	-	+	-	+	+	+	+	+	+	+	+	+		
Hydrochloric Acid	HCl	10			40	-	o	-	+	+	+	+	+	o	+	+	+		
Hydrochloric Acid	HCl	10			60	-	o	-	+	+	+	+	+	-	+	+	+		
Hydrochloric Acid	HCl	30	1,15		20	-	+	-	+	+	+	+	+	-	+	+	+		
Hydrochloric Acid	HCl	30			40	-	o	-	+	+	+	+	+	-	o	+	+		
Hydrochloric Acid	HCl	30			60	-	o	-	+	+	+	+	o	-	o	+	+		
Hydrochloric Acid	HCl	conc.	1,20		20	-	+	-	+	+	+	+	+	-	+	+	+		
Hydrochloric Acid	HCl	conc.			40	-	o	-	+	+	+	+	+	-	o	+	+		
Hydrochloric Acid	HCl	conc.			60	-	o	-	o	+	+	o	o	-	o	+	+		
Hydrocyanic Acid	HCN	TR	0,69		20	+	+	-	+	+	+	+	+	o	+	+	+		
Hydrocyanic Acid	HCN	GL			20	+	+	-	+	+	+	+	o	-	o	+	+		
Hydrocyanic Acid	HCN	GL			40	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	o	o	-	o	+	+		
Hydrocyanic Acid	HCN	GL			60	o	+	-	+ <sup>1)</sup>	+	+	o	o	-	o	+	+		
Hydrofluoric Acid	HF	40	1,06		20	-	o	-	+ <sup>1)</sup>	+	+	-	+	-	o	+	+		

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hasleloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FFP	FFKM		
Hydrofluoric Acid	HF	40			40	- o	- + <sup>1)</sup>	+ +	- +	- +	- +	- +	- +	- +	- +	+ +			
Hydrofluoric Acid	HF	40			60	- o	- o	+ +	+ +	- o	- o	- o	- o	- o	- o	+ +			
Hydrofluoric Acid	HF	60			20	- o	- +	+ +	+ +	- +	- +	- +	- +	- o	+ +	+ +			
Hydrofluoric Acid	HF	70	1,23		20	- o	- o	+ +	+ +	- o	- o	- o	- o	- o	+ +	+ +			
Hydrofluoric Acid	HF	70			40	- o	- o	+ +	+ +	- o	- o	- o	- o	- o	- o	+ +			
Hydrofluoric Acid	HF	70			60	- o	- o	+ o	+ +	- o	- o	- o	- o	- o	- o	+ +			
Hydrofluosilic Acid	H <sub>2</sub> SiF <sub>6</sub>	32	1,17		20	- +	- + <sup>1)</sup>	+ +	+ +	- +	- +	- +	- +	- o	+ +	+ +			
Hydrofluosilic Acid	H <sub>2</sub> SiF <sub>6</sub>	32			40	- o	- + <sup>1)</sup>	+ +	+ +	- +	- +	- +	- +	- o	+ +	+ +			
Hydrofluosilic Acid	H <sub>2</sub> SiF <sub>6</sub>	32			60	- o	- + <sup>1)</sup>	+ +	+ +	- +	- +	- +	- +	- o	+ +	+ +			
Hydrogen Fluoride					See Hydrofluoric Acid														
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	3	1,01		20	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ o	+ +	+ +	+ +	+ +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	3			40	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ o	- +	+ +	+ +	+ +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	3			60	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ o	- o	+ +	+ +	+ +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	10	1,04		20	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ o	+ +	+ +	+ +	+ +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	10			40	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ o	- o	+ +	+ +	+ +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	10			60	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ o	- o	+ +	+ +	+ +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	20	1,07		20	+ <sup>1)</sup> +	+ + <sup>1)</sup>	+ +	+ +	+ o	+ o	+ o	+ +	+ +	+ +	+ +	+ +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	20			40	+ <sup>1)</sup> +	+ + <sup>1)</sup>	+ +	+ +	+ o	+ o	+ o	- o	+ +	+ +	+ +	+ +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	20			60	+ <sup>1)</sup> +	+ + <sup>1)</sup>	+ +	+ +	+ o	+ o	+ o	- -	+ +	+ +	+ +	+ +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	30	1,11		20	+ <sup>1)</sup> +	+ + <sup>1)</sup>	+ +	+ +	+ o	+ o	+ o	- +	+ +	+ +	+ +	+ +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	30			40	+ <sup>1)</sup> +	+ + <sup>1)</sup>	+ +	+ +	+ o	+ o	+ o	- o	+ +	+ +	+ +	+ +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	30			60	+ <sup>1)</sup> +	+ + <sup>1)</sup>	+ +	+ +	+ o	+ o	+ o	- o	+ +	+ +	+ +	+ +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	90	1,42		20	+ <sup>1)</sup> +	+ +	- +	+ +	- +	- +	- +	- +	- +	- +	- +	- +		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	90			40	+ <sup>1)</sup> +	+ +	- +	+ +	- o	+ -	- o	- o	- o	- o	- o	- o		
Hydrogen Peroxide	H <sub>2</sub> O <sub>2</sub>	90			60	+ <sup>1)</sup> +	+ +	- +	+ +	- o	+ -	- o	- o	- o	- o	- o	- o		
Hydroxy Acetic Acid					See Glycolic Acid														
Hydroxybenzene					See Phenol														
Hydroxysuccinic Acid	HOOC-CH <sub>2</sub> -CHOH-COOH	50			20	+ <sup>1)</sup> +	- + <sup>1)</sup>	+ +	+ +	+ o	+ +	+ +	+ +	+ +	+ +	+ +	+ +		
Hydroxysuccinic Acid	HOOC-CH <sub>2</sub> -CHOH-COOH	50			40	+ <sup>1)</sup> +	- + <sup>1)</sup>	+ +	+ +	+ o	+ +	+ +	+ +	+ +	+ +	+ +	+ +		
Hydroxysuccinic Acid	HOOC-CH <sub>2</sub> -CHOH-COOH	50			60	+ <sup>1)</sup> +	- + <sup>1)</sup>	+ +	+ +	+ o	+ +	+ +	+ +	+ +	+ +	+ +	+ +		
Ink		H	1,00		20	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +		
Iodine Preparations		H			20	o +	o +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	o		
Iodine Preparations		H			40	o +	o +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	o		
Iodine Preparations		H			60	o +	o +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	o		
Iodoform					See Triiodine Methane														
Iron Vitriol					See Ferrosulphate														
Isobutanol					See Isobutyl Alcohol														
Isobutyl Alcohol	C <sub>4</sub> H <sub>10</sub> O	100	0,81	All	20	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	- +	+ +	+ +	+ +		
Isobutyl Alcohol	C <sub>4</sub> H <sub>10</sub> O	100			40	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	- +	+ +	+ +	+ +		
Isobutyl Alcohol	C <sub>4</sub> H <sub>10</sub> O	100			60	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	- +	+ +	+ +	+ +		
Isocyanate					20	+ +	+ +	- -	- -	+ o	+ +	+ +	- +	- +	+ +	+ +	+ +		
Isooctane	C <sub>8</sub> H <sub>18</sub>	TR		AI	20	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ +		
Isooctanol	C <sub>8</sub> H <sub>19</sub> -CH(C <sub>2</sub> H <sub>5</sub> )	TR	0,83	AllI	20	+ +	+ +	+ +	+ +	+ +	+ +	+ +	+ o	+ +	+ +	+ +	+ +		
Isopropanol					See Propanol														
Isopropyl Acetate	C <sub>5</sub> H <sub>10</sub> O <sub>2</sub>		0,87	AI	20	+ <sup>1)</sup> +	- o	- o	+ +	+ +	+ o	-	+ +	+ +	+ +	+ +	+ +		
Isopropyl Ether	C <sub>3</sub> H <sub>8</sub> O	TR	0,73	AI	20	+ <sup>1)</sup> +	- o	- o	+ +	+ +	- -	- -	- -	- -	- -	- +	+ +		
Isopropyl Ether	C <sub>3</sub> H <sub>8</sub> O	TR			40	+ <sup>1)</sup> +	- o	- o	- o	+ +	- -	- -	- -	- -	- -	+ +	+ +		
Isopropyl Ether	C <sub>3</sub> H <sub>8</sub> O	TR			60	+ <sup>1)</sup> +	- o	- o	- o	+ +	- -	- -	- -	- -	- -	+ +	+ +		
Kerosene					See Naphtha														
Kerosine					See Naphtha														

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm <sup>3</sup> ]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM
Lactic Acid	C <sub>3</sub> H <sub>6</sub> O <sub>3</sub>	10			20	+	+	-	+	+	+	+	+	o	+	+	+
Lactic Acid	C <sub>3</sub> H <sub>6</sub> O <sub>3</sub>	10			40	+	+	-	+	+	+	+	+	-	+	+	+
Lactic Acid	C <sub>3</sub> H <sub>6</sub> O <sub>3</sub>	10			60	+	+	-	+	+	+	+	+	-	+	+	+
Lactic Acid	C <sub>3</sub> H <sub>6</sub> O <sub>3</sub>	90			20	+	+	-	+	+	+	+	+	-	+	+	+
Lactic Acid	C <sub>3</sub> H <sub>6</sub> O <sub>3</sub>	90			40	o	+	-	+	o	+	+	+	-	+	+	+
Lactic Acid	C <sub>3</sub> H <sub>6</sub> O <sub>3</sub>	90			60	o	+	-	+	o	+	+	+	-	o	+	+
Lanolin		TR			20	+	+	+	o	+	+	+	+	+	o	+	+
Lanolin		TR			40	+	+	+	-	+	+	+	+	-	+	+	+
Lanolin		TR			60	+	+	+	-	+	+	+	+	o	-	+	+
Lauric Acid	C <sub>12</sub> H <sub>24</sub> O <sub>2</sub>	TR			20	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	-	+	-	-	+	+
Lauric Acid	C <sub>12</sub> H <sub>24</sub> O <sub>2</sub>	TR			40	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	-	+	-	-	+	+
Lauric Acid	C <sub>12</sub> H <sub>24</sub> O <sub>2</sub>	TR			60	+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	-	+	-	-	+	+
Lead Acetate	C <sub>4</sub> H <sub>6</sub> O <sub>4</sub> Pb	10			20	+	+	-	+	+	+	+	+	+	+	+	+
Lead Acetate	C <sub>4</sub> H <sub>6</sub> O <sub>4</sub> Pb	10			40	+	+	-	+	+	+	+	+	+	+	+	+
Lead Acetate	C <sub>4</sub> H <sub>6</sub> O <sub>4</sub> Pb	10			60	+	+	-	+	+	+	+	+	+	+	+	+
Lead Acetate	C <sub>4</sub> H <sub>6</sub> O <sub>4</sub> Pb	GL			20	+	+	-	+	+	+	+	+	+	+	+	+
Lead Acetate	C <sub>4</sub> H <sub>6</sub> O <sub>4</sub> Pb	GL			40	+	+	-	+	+	+	+	+	+	+	+	+
Lead Acetate	C <sub>4</sub> H <sub>6</sub> O <sub>4</sub> Pb	GL			60	+	+	-	+	+	+	+	+	+	+	+	+
Lead Nitrate	Pb(NO <sub>3</sub> ) <sub>2</sub>	50			20	+	+	+	+	+	+	+	+	+	+	+	+
Lead Sugar						See Lead Acetate											
Lead Tetraethyl	Pb(C <sub>2</sub> H <sub>5</sub> ) <sub>4</sub>	TR	1,66	AllI	20	+	+	+	+	+	+	+	+	o	+	+	
Linseed Oil		TR			20	+	+	+	+	+	+	+	+	+	+	+	+
Linseed Oil		TR			40	+	+	+	+	+	+	+	+	o	+	+	
Linseed Oil		TR			60	+	+	+	o	+	+	+	+	-	+	+	
Lithium Chloride	LiCl	45	1,30		20	o	+	-	+	+	+	+	+	+	+	+	+
Lithium Chloride	LiCl	45			40	o	+	-	+	+	+	+	+	+	+	+	+
Lithium Chloride	LiCl	45			60	-	o	-	+	+	+	+	+	+	+	+	+
Lithium Sulphate	LiSO <sub>4</sub>	25	1,23		20	+	+	+	+	+	+	+	+	+	+	+	+
Lithium Sulphate	LiSO <sub>4</sub>	25			40	+	+	+	+	+	+	+	+	+	+	+	+
Lithium Sulphate	LiSO <sub>4</sub>	25			60	+	+	+	+	+	+	+	+	+	+	+	+
Lunar Caustic						See Silver Nitrate											
Magnesium Chloride	MgCl <sub>2</sub>	10			20	o	+	-	+	+	+	+	+	+	+	+	+
Magnesium Chloride	MgCl <sub>2</sub>	10			40	o	+	-	+	+	+	+	+	+	+	+	+
Magnesium Chloride	MgCl <sub>2</sub>	10			60	o	+	-	+	+	+	+	+	+	+	+	+
Magnesium Chloride	MgCl <sub>2</sub>	GL			20	o	+	-	+	+	+	+	+	+	+	+	+
Magnesium Chloride	MgCl <sub>2</sub>	GL			40	o	+	-	+	+	+	+	+	+	+	+	+
Magnesium Chloride	MgCl <sub>2</sub>	GL			60	o	+	-	+	+	+	+	+	+	+	+	+
Magnesium Nitrate	Mg(NO <sub>3</sub> ) <sub>2</sub>	25	1,21		20	+	+	+	+	+	+	+	+	+	+	+	+
Magnesium Nitrate	Mg(NO <sub>3</sub> ) <sub>2</sub>	25			40	+	+	+	+	+	+	+	+	+	+	+	+
Magnesium Nitrate	Mg(NO <sub>3</sub> ) <sub>2</sub>	25			60	+	+	+	+	+	+	+	+	+	+	+	+
Magnesium Sulphate	MgSO <sub>4</sub>	10			20	+	+	+	+	+	+	+	+	+	+	+	+
Magnesium Sulphate	MgSO <sub>4</sub>	10			40	+	+	+	+	+	+	+	+	+	+	+	+
Magnesium Sulphate	MgSO <sub>4</sub>	10			60	+	+	+	+	+	+	+	+	+	+	+	+
Magnesium Sulphate	MgSO <sub>4</sub>	GL	1,28		20	+	+	+	+	+	+	+	+	+	+	+	+
Magnesium Sulphate	MgSO <sub>4</sub>	GL			40	+	+	+	+	+	+	+	+	+	+	+	+
Magnesium Sulphate	MgSO <sub>4</sub>	GL			60	+	+	+	+	+	+	+	+	+	+	+	+
Maleic Acid	C <sub>4</sub> H <sub>2</sub> O <sub>4</sub>	35			20	+	+	-	+	+	+	+	+	-	+	+	+
Maleic Acid	C <sub>4</sub> H <sub>2</sub> O <sub>4</sub>	35			40	+	+	-	+	+	+	+	+	-	+	+	+
Maleic Acid	C <sub>4</sub> H <sub>2</sub> O <sub>4</sub>	GL			20	+	+	-	+	+	+	+	+	-	o	+	+
Maleic Acid	C <sub>4</sub> H <sub>2</sub> O <sub>4</sub>	GL			40	+	+	-	+	+	+	+	+	-	-	+	+

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM	
Maleic Acid	C <sub>4</sub> H <sub>4</sub> O <sub>4</sub>	GL		60	+ + -	+ + + + + + + + + + + + + +						- - + - + + + + + + + + + +					
Malic Acid					See Hydrosuccinic Acid												
Manganous Chloride	MnCl <sub>2</sub>	20	1,19		20	o + -	+ + + + + + + + + + + + + +										
Manganous Chloride	MnCl <sub>2</sub>	20			40	o + -	+ + + + + + + + + + + + + +										
Manganous Chloride	MnCl <sub>2</sub>	20			60	- o -	+ + + + + + + + + + + + + +										
Mercury Cyanide	Hg(CN) <sub>2</sub>	TR			20	+ + -	+ + + + + + + + + + + + + +										
Mercury Cyanide	Hg(CN) <sub>2</sub>	TR			40	+ + -	+ + + + + + + + + + + + + +										
Mercury Cyanide	Hg(CN) <sub>2</sub>	TR			60	+ + -	+ + + + + + + + + + + + + +										
Mercury Nitrate	Hg(NO <sub>3</sub> ) <sub>2</sub>	GL			20	+ + -	+ + + + + + + + + + + + + +										
Mercury Nitrate	Hg(NO <sub>3</sub> ) <sub>2</sub>	GL			40	+ + -	+ + + + + + + + + + + + + +										
Mercury Nitrate	Hg(NO <sub>3</sub> ) <sub>2</sub>	GL			60	+ + -	+ + + + + + + + + + + + + +										
Methanol	CH <sub>3</sub> OH	TR		B	20	+ + + + + + + + + + o o o + + +											
Methanol	CH <sub>3</sub> OH	TR			40	+ + + + + + + + + + o o o + + +											
Methanol	CH <sub>3</sub> OH	TR			60	+ + o + + + + + + + o - o + +											
Methyl Alcohol					See Methanol												
Methyl Benzene					See Toluene												
Methyl Cellosolve					See Methyl Glycol												
Methyl Cyanide					See Acetonitrile												
Methyl Ester					See Acetic Methyl Ester												
Methyl Ethyl Ketone (MEK)					See Butanone												
Methyl Glycol	(CH <sub>2</sub> ) <sub>2</sub> HOCH <sub>3</sub>		0,98		20	+ + + + + + + + + + + + + +											
Methyl Glycol	(CH <sub>2</sub> ) <sub>2</sub> HOCH <sub>3</sub>				40	+ + + + + + + + + + + + + +											
Methyl Glycol	(CH <sub>2</sub> ) <sub>2</sub> HOCH <sub>3</sub>				60	+ + + + + + + + + + + + + +											
Methyl Isobutyl Ketone (MIBK)	C <sub>6</sub> H <sub>11</sub> O			All	20	+ + - - + + + + o o o o + +											
Methyl Pentanon					See Methyl Isobutyl Ketone (MIBK)												
Methyl Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub> -CH <sub>2</sub>	50			20	o o - o + + + - o - + + +											
Methyl Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub> -CH <sub>2</sub>	50			40	- o - o + + + + + + + + + +											
Methyl Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub> -CH <sub>2</sub>	50			60	- - - - + + + + + + + + + +											
Methyl Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub> -CH <sub>2</sub>	TR			20	o o - - + + + - o - + + +											
Methyl Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub> -CH <sub>2</sub>	TR			40	- o - - + + + - o - + + +											
Methyl Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub> -CH <sub>2</sub>	TR			60	- o - - + + + - o - + + +											
Methylene Chloride	CH <sub>2</sub> Cl <sub>2</sub>		1,33		20	+ + - o o + <sup>1)</sup> + o - o - o + +											
Methylene Chloride	CH <sub>2</sub> Cl <sub>2</sub>				40	+ + - o o + <sup>1)</sup> + o - o - o + +											
Milk					20	+ + + + + + + + + + + + + +											
Milk of Lime					See Calcium Hydroxyde												
Mineral Oils						20	+ + + + + + + + + + + + + +										
Mineral Oils						40	+ + + + + + + + + + + + + +										
Mineral Oils						60	+ + + o + + + + + + + + + +										
Mineral Water						20	+ + + + + + + + + + + + + +										
Mineral Water						40	+ + + + + + + + + + + + + +										
Mineral Water						60	+ + + + + + + + + + + + + +										
Mirbane					See Nitrobenzene												
Monochloracetic Acid					See Chloroacetic Acid												
Muriatic Acid					See Hydrochloric Acid												
Naphta		TR	0,81	All	20	+ <sup>1)</sup> + + + + + + + + + + + +											
Naphta		TR			40	+ <sup>1)</sup> + + + + + + + + + + + +											
Naphta		TR			60	+ <sup>1)</sup> + + + + + + + + + + + +											
Naphthenic Acid					See Fatty Acids												
Nickel Chloride	NiCl <sub>2</sub>	20	1,22		20	o + - + + + + + + + + + + +											
Nickel Chloride	NiCl <sub>2</sub>	20			40	o + - + + + + + + + + + + +											

TR = technically pure, GL = saturated solution, H = commercial composition  
 + = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM
Nickel Chloride	NiCl₂	20			60	o + - + + + + + + o + + +											
Nickel Nitrate	Ni(NO₃)₂	35	1,38		20	+ + - + + + + + + + + + +											
Nickel Nitrate	Ni(NO₃)₂	35			40	+ + - + + + + + + + + + +											
Nickel Nitrate	Ni(NO₃)₂	35			60	+ + - + + + + + + + + + +											
Nickel Sulphate	NiSO₄	10	1,21		20	+ + - + + + + + + + + + +											
Nickel Sulphate	NiSO₄	10			40	+ + - + + + + + + + + + +											
Nickel Sulphate	NiSO₄	10			60	+ + - + + + + + + + + + +											
Nicotine	C₁₀H₁₄N₂				20	+ + - - - + + + + o + + +											
Nitric Acid	HNO₃	10	1,05		20	+¹⁾ + - + + + o + + + +											
Nitric Acid	HNO₃	10			40	+¹⁾ + - o + + o + + + +											
Nitric Acid	HNO₃	10			60	+¹⁾ + - o + + o + + + +											
Nitric Acid	HNO₃	30	1,18		20	+¹⁾ + - o + + + + - + - +											
Nitric Acid	HNO₃	30			40	+¹⁾ + - o + + + + - + - +											
Nitric Acid	HNO₃	30			60	o + - - + + - + - + - o + +											
Nitric Acid	HNO₃	50	1,31		20	+¹⁾ + - o + + + + - + - +											
Nitric Acid	HNO₃	50			40	o + - - + + + - o - - + +											
Nitric Acid	HNO₃	50			60	o o - - + + + - o - - o - - +											
Nitric Acid	HNO₃	65	1,41		20	+¹⁾ + - o + + + + - + - o - - +											
Nitric Acid	HNO₃	65			40	o + - - + + + - o - - o - - +											
Nitric Acid	HNO₃	65			60	o o - - + + + - o - - o - - +											
Nitrobenzene	C₆H₅NO₂	TR	1,21	AIII	20	+ + + + + + + + + o o o + +											
Nitrobenzene	C₆H₅NO₂	TR			40	+ + + o + + + + + o o o - + +											
Nitrobenzene	C₆H₅NO₂	TR			60	+ + + o + + + + + o o o - - +											
Nitrotoluene	C₆H₄CH₃NO₂	TR			20	+ + + + + + + + + o o o o + +											
Nitrotoluene	C₆H₄CH₃NO₂	TR			40	+ + + + + + + + + o o o o - + +											
Nitrotoluene	C₆H₄CH₃NO₂	TR			60	+ + + o + + + + + o o o o - + +											
Nitrous Acid	HNO₂				20	o + - o + + + + + + + + - o + +											
Nitrous Acid	HNO₂				40	o + - o + + + + + + + + - o + +											
Nitrous Acid	HNO₂				60	o + - o + + + + + + + + - o + +											
Octal						See Diethyl Phthalate											
Octane	C₈H₁₈	TR		AI	20	+ + + + + + + + + + + + + + + +											
Oil						See Mineral Oils											
Oleic Acid	C₁₈H₃₄O₂	TR	0,90		20	+ + - + + + + + + + o - + +											
Oleic Acid	C₁₈H₃₄O₂	TR			40	+ + - + + + + + + + o o - + +											
Oleic Acid	C₁₈H₃₄O₂	TR			60	+ + - o + + + + + + o o - - +											
Oleum	H₂SO₄+SO₃				20	+¹⁾ + - - - + + + + + + + + + +											
Oxalic Acid	(CO₂H)₂	10			20	+ + - + + + + + + + + + + + +											
Oxalic Acid	(CO₂H)₂	10			40	+ + - o + + + + + + + + + + + +											
Oxalic Acid	(CO₂H)₂	10			60	+ + - o + + + + + + + + + + + +											
Oxalic Acid	(CO₂H)₂	GL	1,65		20	+¹⁾ + - + + + + + + + + + + + +											
Oxalic Acid	(CO₂H)₂	GL			40	+¹⁾ + - o + + + + + + + + + + + +											
Oxalic Acid	(CO₂H)₂	GL			60	+¹⁾ + - o o + o + + o o + o o + +											
Palatinol C						See Dibutyl Phthalate											
Paraffin Oil	CnH₂n	TR	0,93		20	+ + + + + + + + + + + + + + + +											
Paraffin Oil	CnH₂n	TR			40	+ + + + + + + + + + + + + + + +											
Paraffin Oil	CnH₂n	TR			60	+ + + + + + + + + + + + + + + +											
Pectine		10			20	+ + + + + + + + + + + + + + + +											
Pentanol, 1-Pentanol						See Amyl Alcohol											
Pentyl Acetate						See Amyl Acetate											
Pentyl Chloride						See Amyl Chloride											

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant, ¹⁾ Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM
Peracetic Acid		TR			20	+	-	-	+	+	-	-	-	-	+	-
Peracetic Acid		TR			40	+	-	-	+	+	-	-	-	-	+	-
Peracetic Acid		TR			60	+	-	-	+	+	-	-	-	-	+	-
Perchloric Acid	HClO <sub>4</sub>	20			20	+	+	-	+	+	+	+	-	+	+	+
Perchloric Acid	HClO <sub>4</sub>	20			40	+	+	-	+	+	+	+	-	+	+	+
Perchloric Acid	HClO <sub>4</sub>	20			60	+	+	-	+	+	+	+	o	-	o	+
Perchloric Acid	HClO <sub>4</sub>	50	1,40		20	+	+	-	+	+	+	+	-	+	+	+
Perchloric Acid	HClO <sub>4</sub>	50			40	+	+	-	+	+	+	+	-	+	+	+
Perchloric Acid	HClO <sub>4</sub>	50			60	+	+	-	o	+	+	+	o	-	o	+
Perchloric Acid	HClO <sub>4</sub>	70	1,55		20	+	+	-	+	+	+	+	-	+	+	+
Perchloric Acid	HClO <sub>4</sub>	70			40	+	+	-	+	+	+	+	-	+	+	+
Perchloric Acid	HClO <sub>4</sub>	70			60	+	+	-	+	+	+	+	-	+	+	+
Perchloric Acid	HClO <sub>4</sub>	GL			20	+	+	-	+	+	+	+	-	+	+	+
Perchloric Acid	HClO <sub>4</sub>	GL			40	+	+	-	o	+	+	+	-	+	+	+
Perchloric Acid	HClO <sub>4</sub>	GL			60	o	+	-	-	+	+	+	-	+	+	+
Perchloroethylene	C <sub>2</sub> Cl <sub>4</sub>	TR			20	+	+	-	-	+	+ <sup>1)</sup>	+	+	-	-	+
Perchloroethylene	C <sub>2</sub> Cl <sub>4</sub>	TR			40	+	+	-	-	+	+ <sup>1)</sup>	+	+	-	-	+
Perchloroethylene	C <sub>2</sub> Cl <sub>4</sub>	TR			60	o	+	-	-	+	+ <sup>1)</sup>	+	+	-	-	+
Petrol		H	0,73	AI	20	+	+	+	-	+	+	+	+	-	+	+
Petrol		H			40	+	+	+	-	+	+	+	+	-	+	+
Petrol		H			60	+	+	+	-	+	+	+	+	-	+	+
Petroleum Crude					20	+	+	+	+	+	+	+	+	-	+	+
Petroleum Crude					40	+	+	+	+	+	+	+	+	-	+	+
Petroleum Crude					60	+	+	+	+	+	+	+	+	-	+	+
Petroleum Ether		TR	0,69	AI	20	+	+	+	-	+	+	+	+	o	+	+
Petroleum Ether		TR			40	+	+	+	-	+	+	+	+	o	-	+
Petroleum Ether		TR			60	+	+	+	-	+	+	+	o	-	-	+
Phenol	C <sub>6</sub> H <sub>5</sub> O	100			20	+	+	+	+	+	+	+	+	+	+	+
Phenol	C <sub>6</sub> H <sub>5</sub> O	100			40	+	+	+	+	+	+	+	+	o	+	+
Phenol	C <sub>6</sub> H <sub>5</sub> O	100			60	+	+	+	+	+	+	+	+	o	+	+
Phenol	C <sub>6</sub> H <sub>5</sub> O	50			20	+	+	+	+	+	+	+	+	+	+	+
Phenol	C <sub>6</sub> H <sub>5</sub> O	50			40	+	+	+	+	+	+	+	+	o	+	+
Phenol	C <sub>6</sub> H <sub>5</sub> O	50			60	+	+	+	+	+	+	+	+	o	+	+
Phenol	C <sub>6</sub> H <sub>5</sub> O	90			20	+	+	+	+	+	+	+	+	-	+	+
Phenol	C <sub>6</sub> H <sub>5</sub> O	90			40	+	+	+	+	+	+	+	o	-	+	+
Phenol	C <sub>6</sub> H <sub>5</sub> O	90			60	+	+	+	+	+	+	+	o	-	+	+
Phenyl Chloride						See Chlorobenzene										
Phosphor Chloride						See Phosphorous Trichloride										
Phosphoric Acid	H <sub>3</sub> PO <sub>4</sub>	30	1,18		20	+	+	-	+	+	+	+	+	o	+	+
Phosphoric Acid	H <sub>3</sub> PO <sub>4</sub>	30			40	+	+	-	+	+	+	+	+	o	+	+
Phosphoric Acid	H <sub>3</sub> PO <sub>4</sub>	30			60	+	+	-	+	+	+	+	-	+	+	+
Phosphoric Acid	H <sub>3</sub> PO <sub>4</sub>	50			20	+	+	-	+	+	+	+	+	o	+	+
Phosphoric Acid	H <sub>3</sub> PO <sub>4</sub>	50			40	+	+	-	+	+	+	+	+	o	+	+
Phosphoric Acid	H <sub>3</sub> PO <sub>4</sub>	50			60	o	+	-	+	+	+	+	-	+	+	+
Phosphoric Acid	H <sub>3</sub> PO <sub>4</sub>	85	1,69		20	+	+	-	+	+	+	+	-	+	+	+
Phosphoric Acid	H <sub>3</sub> PO <sub>4</sub>	85			40	+	+	-	+	+	+	+	-	+	+	+
Phosphoric Acid	H <sub>3</sub> PO <sub>4</sub>	85			60	o	+	-	+	+	+	+	-	+	+	+
Phosphoric Acid	H <sub>3</sub> PO <sub>4</sub>	95	1,70		20	-	+	-	+	+	+	+	o	+	-	o
Phosphoric Acid	H <sub>3</sub> PO <sub>4</sub>	95			40	-	+	-	o	+	+	o	+	-	o	+
Phosphoric Acid	H <sub>3</sub> PO <sub>4</sub>	95			60	-	o	-	-	+	+	o	o	-	o	+

TR = technically pure, GL = saturated solution, H = commercial composition  
 + = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hasleloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM	
Phosphorous Trichloride	POCl <sub>3</sub>	TR	1,57		20	+	+	-	+	+	+	+	+	-	+	+	+	
Phosphorous Trichloride	POCl <sub>3</sub>	TR			40	o	o	-	o	+	+	+	+	-	+	+	+	
Phosphorous Trichloride	POCl <sub>3</sub>	TR			60	-	-	-	o	+	+	+	+	-	+	+	+	
Phthalic Acid	C <sub>6</sub> H <sub>4</sub> (COOH) <sub>2</sub> +H <sub>2</sub> O	50			20	+	+	-	+	+	+	+	+	-	+	+	+	
Phthalic Acid	C <sub>6</sub> H <sub>4</sub> (COOH) <sub>2</sub> +H <sub>2</sub> O	50			40	+	+	-	+	+	+	+	+	-	+	+	+	
Phthalic Acid	C <sub>6</sub> H <sub>4</sub> (COOH) <sub>2</sub> +H <sub>2</sub> O	50			60	+	+	-	+	+	+	+	+	-	+	+	+	
Phthalic Acid	C <sub>6</sub> H <sub>4</sub> (COOH) <sub>2</sub> +H <sub>2</sub> O	GL	1,59		20	+	+	-	+	+	+	+	o	-	+	+	+	
Phthalic Acid	C <sub>6</sub> H <sub>4</sub> (COOH) <sub>2</sub> +H <sub>2</sub> O	GL			40	+	+	-	+	+	+	+	o	-	+	+	+	
Phthalic Acid	C <sub>6</sub> H <sub>4</sub> (COOH) <sub>2</sub> +H <sub>2</sub> O	GL			60	+	+	-	+	+	+	+	-	o	+	+	+	
Pine Needle Oil					See Essential Oils													
Polyhydric Alcohol			1,78		20	+	+	+	-	+	+	+	+	+	+	+	+	+
Potash					See Potassium Carbonate													
Potash Bleaching Solution					See Potassium Hypochlorite													
Potassium Aluminium Sulphate	KAl(SO <sub>4</sub> ) <sub>2</sub> ·2H <sub>2</sub> O	50			20	+	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Aluminium Sulphate	KAl(SO <sub>4</sub> ) <sub>2</sub> ·2H <sub>2</sub> O	50			40	+	+	+	+	+	+	+	+	o	+	+	+	
Potassium Aluminium Sulphate	KAl(SO <sub>4</sub> ) <sub>2</sub> ·2H <sub>2</sub> O	50			60	+	+	+	+	+	+	+	+	-	+	+	+	
Potassium Bichromate					See Potassium Dichromate													
Potassium Bromate	KBrO <sub>3</sub> +H <sub>2</sub> O	GL			20	+	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Bromate	KBrO <sub>3</sub> +H <sub>2</sub> O	GL			40	+	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Bromate	KBrO <sub>3</sub> +H <sub>2</sub> O	GL			60	+	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Bromide	KBr + H <sub>2</sub> O	10	1,37		20	+	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Bromide	KBr + H <sub>2</sub> O	10			40	+	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Bromide	KBr + H <sub>2</sub> O	10			60	o	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Bromide	KBr + H <sub>2</sub> O	GL			20	+	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Bromide	KBr + H <sub>2</sub> O	GL			40	+	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Bromide	KBr + H <sub>2</sub> O	GL			60	o	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Carbonate	K <sub>2</sub> CO <sub>3</sub>	GL			20	+	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Carbonate	K <sub>2</sub> CO <sub>3</sub>	GL			40	+	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Carbonate	K <sub>2</sub> CO <sub>3</sub>	GL			60	+	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Chlorate	KClO <sub>3</sub>	50			20	+	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Chlorate	KClO <sub>3</sub>	50			40	+	+	-	+	+	+	+	+	+	o	+	+	+
Potassium Chlorate	KClO <sub>3</sub>	50			60	o	+	-	+	+	+	+	+	-	+	+	+	+
Potassium Chloride	KCl	10			20	o	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Chloride	KCl	10			40	o	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Chloride	KCl	10			60	o	o	-	+	+	+	+	+	+	+	+	+	+
Potassium Chloride	KCl	GL	1,17		20	o	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Chloride	KCl	GL			40	o	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Chloride	KCl	GL			60	o	o	-	+	+	+	+	+	+	+	+	+	+
Potassium Cyanide	KCN	50			20	+	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Cyanide	KCN	50			40	+	+	-	+	+	+	+	+	o	+	+	+	+
Potassium Cyanide	KCN	50			60	+	+	-	+	+	+	+	+	o	+	+	+	+
Potassium Cyanide	KCN	GL	1,31		20	+	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Cyanide	KCN	GL			40	+	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Cyanide	KCN	GL			60	+	+	-	+	o	+	+	+	+	+	+	+	+
Potassium Dichromate	K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	40			20	+	+	-	+	+	+	+	+	+	+	+	+	+
Potassium Ferricyanide	K <sub>4</sub> Fe(CN) <sub>6</sub>	10			20	+	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Ferricyanide	K <sub>4</sub> Fe(CN) <sub>6</sub>	10			40	+	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Ferricyanide	K <sub>4</sub> Fe(CN) <sub>6</sub>	10			60	+	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Ferricyanide	K <sub>4</sub> Fe(CN) <sub>6</sub>	20	1,11		20	+	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Ferricyanide	K <sub>4</sub> Fe(CN) <sub>6</sub>	20			40	+	+	+	+	+	+	+	+	+	+	+	+	+

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM
Potassium Ferricyanide	K <sub>4</sub> Fe(CN) <sub>6</sub>	20			60	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Ferricyanide	K <sub>4</sub> Fe(CN) <sub>6</sub>	GL			20	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Ferricyanide	K <sub>4</sub> Fe(CN) <sub>6</sub>	GL			40	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Ferricyanide	K <sub>4</sub> Fe(CN) <sub>6</sub>	GL			60	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Ferrocyanide	K <sub>3</sub> Fe(CN) <sub>6</sub>	10			20	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	+	+	o	+	+	+	+	+
Potassium Ferrocyanide	K <sub>3</sub> Fe(CN) <sub>6</sub>	10			40	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	+	+	o	+	+	+	+	+
Potassium Ferrocyanide	K <sub>3</sub> Fe(CN) <sub>6</sub>	10			60	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	+	+	o	+	+	+	+	+
Potassium Ferrocyanide	K <sub>3</sub> Fe(CN) <sub>6</sub>	16	1,11		20	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	+	+	o	+	+	+	+	+
Potassium Ferrocyanide	K <sub>3</sub> Fe(CN) <sub>6</sub>	16			40	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	+	+	o	+	+	+	+	+
Potassium Ferrocyanide	K <sub>3</sub> Fe(CN) <sub>6</sub>	16			60	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	+	+	o	+	+	+	+	+
Potassium Ferrocyanide	K <sub>3</sub> Fe(CN) <sub>6</sub>	GL			20	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	+	+	o	+	+	+	+	+
Potassium Ferrocyanide	K <sub>3</sub> Fe(CN) <sub>6</sub>	GL			40	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	+	+	o	+	+	+	+	+
Potassium Ferrocyanide	K <sub>3</sub> Fe(CN) <sub>6</sub>	GL			60	+ <sup>1)</sup>	+	+	+ <sup>1)</sup>	+	+	o	+	+	+	+	+
Potassium Hydroxide	KOH	20	1,19		20	+	+	-	+	+	+	-	o	+	+	+	+
Potassium Hydroxide	KOH	20			40	+	+	-	+	+	+	-	o	o	+	+	+
Potassium Hydroxide	KOH	20			60	+	+	-	+	+	+	-	o	o	+	+	+
Potassium Hydroxide	KOH	30	1,29		20	+	+	-	+	+	+	-	o	+	+	+	+
Potassium Hydroxide	KOH	30			40	+	+	-	+	+	+	-	o	o	+	+	+
Potassium Hydroxide	KOH	30			60	+	+	-	+	+	+	-	o	o	+	+	+
Potassium Hydroxide	KOH	60	1,63		20	+	+	-	+	+	+	-	-	+	+	+	+
Potassium Hydroxide	KOH	60			40	+	+	-	+	+	+	-	-	-	+	+	+
Potassium Hydroxide	KOH	60			60	+	+	-	+	+	+	-	-	-	+	+	+
Potassium Hydroxide	KOH	60			60	+	+	-	+	+	+	-	-	-	+	+	+
Potassium Hypochlorite	KClO	15			20	o	+	-	o	+	+	+	-	+	+	+	+
Potassium Hypochlorite	KClO	15			40	o	+	-	o	+	+	+	-	o	+	+	+
Potassium Hypochlorite	KClO	15			60	o	o	-	-	+	+	+	-	-	+	+	+
Potassium Iodide	KJ	50	1,55		20	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Iodide	KJ	50			40	+	+	+	+	+	+	+	+	o	+	+	+
Potassium Iodide	KJ	50			60	o	+	+	+	+	+	+	+	o	+	+	+
Potassium Iodide	KJ	GL			20	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Iodide	KJ	GL			40	+	+	+	+	+	+	+	+	o	+	+	+
Potassium Iodide	KJ	GL			60	o	+	o	+	+	+	+	+	o	+	+	+
Potassium Nitrate	KNO <sub>3</sub>	10			20	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Nitrate	KNO <sub>3</sub>	10			40	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Nitrate	KNO <sub>3</sub>	10			60	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Nitrate	KNO <sub>3</sub>	24	1,17		20	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Nitrate	KNO <sub>3</sub>	24			40	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Nitrate	KNO <sub>3</sub>	24			60	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Oxalate	K <sub>2</sub> (CO <sub>2</sub> ) <sub>2</sub>				20	+	+	-	+	+	+	+	+	-	+	+	+
Potassium Oxalate	K <sub>2</sub> (CO <sub>2</sub> ) <sub>2</sub>				40	+	+	-	+	+	+	+	+	-	+	+	+
Potassium Oxalate	K <sub>2</sub> (CO <sub>2</sub> ) <sub>2</sub>				60	+	+	-	+	+	+	+	+	-	+	+	+
Potassium Permanganate	KMnO <sub>4</sub>	6	1,04		20	+	+	+	+	+	+	+	+	o	+	+	+
Potassium Permanganate	KMnO <sub>4</sub>	6			40	+	+	+	+	+	+	+	+	o	+	+	+
Potassium Permanganate	KMnO <sub>4</sub>	6			60	+	+	+	+	+	+	+	+	o	+	+	+
Potassium Permanganate	KMnO <sub>4</sub>	18			20	+	+	+	+	+	+	+	+	o	+	+	+
Potassium Permanganate	KMnO <sub>4</sub>	18			40	+	+	+	+	+	+	+	+	o	+	+	+
Potassium Sulphate	K <sub>2</sub> SO <sub>4</sub>	10	1,08		20	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Sulphate	K <sub>2</sub> SO <sub>4</sub>	10			40	+	+	+	+	+	+	+	+	+	+	+	+
Potassium Sulphate	K <sub>2</sub> SO <sub>4</sub>	10			60	+	+	+	+	+	+	+	+	+	+	+	+
Propanediol						See Propylene Glycol											
Propanone						See Acetone											

TR = technically pure, GL = saturated solution, H = commercial composition  
 + = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM
Propionic Acid	C <sub>3</sub> H <sub>6</sub> O <sub>2</sub>	50			20	+	+	-	+	+	+	+	+	-	o	+	+
Propionic Acid	C <sub>3</sub> H <sub>6</sub> O <sub>2</sub>	50			40	+	+	-	+	+	+	+	+	-	o	+	+
Propionic Acid	C <sub>3</sub> H <sub>6</sub> O <sub>2</sub>	50			60	+	+	-	+	+	+	+	o	-	o	+	+
Propionic Acid	C <sub>3</sub> H <sub>6</sub> O <sub>2</sub>	TR	0,99		20	+	+	-	+	+	+	+	+	-	+	+	+
Propionic Acid	C <sub>3</sub> H <sub>6</sub> O <sub>2</sub>	TR			40	+	+	-	o	+	+	+	+	-	+	+	+
Propionic Acid	C <sub>3</sub> H <sub>6</sub> O <sub>2</sub>	TR			60	+	+	-	o	+	+	+	+	-	o	+	+
Propyl Acetate						See Isopropylacetate											
Propyl Alcohol	C <sub>3</sub> H <sub>8</sub> O	TR		B	20	+	+	+	+	+	+ <sup>1)</sup>	+	+	+	o	+	+
Propyl Alcohol	C <sub>3</sub> H <sub>8</sub> O	TR			40	+	+	+	+	+	+ <sup>1)</sup>	+	+	+	o	+	+
Propyl Alcohol	C <sub>3</sub> H <sub>8</sub> O	TR			60	+	+	+	+	+	+ <sup>1)</sup>	+	+	+	o	+	+
Propylene Aldehyde	C <sub>4</sub> H <sub>6</sub> O	TR		AI	20	+	+	+	-	+	+	+	+	+	+	+	+
Propylene Glycol	C <sub>3</sub> H <sub>8</sub> O <sub>2</sub>	TR	1,04		20	+	+	+	+	+	+	+	+	+	+	+	+
Propylene Glycol	C <sub>3</sub> H <sub>8</sub> O <sub>2</sub>	TR			40	+	+	+	+	+	+	+	+	o	+	+	+
Propylene Glycol	C <sub>3</sub> H <sub>8</sub> O <sub>2</sub>	TR			60	+	+	+	+	+	+	+	+	o	-	+	+
Propylene Oxide	C <sub>3</sub> H <sub>6</sub> O	TR	0,83	AI	20	+	+	+	+	+	+	+	+	-	-	-	+
Propylene Oxide	C <sub>3</sub> H <sub>6</sub> O	TR			40	+	+	+	+	+	+	+	+	-	-	-	+
Prussic Acid						See Hydrocyanic Acid											
Pyranon						See Diacetone Alcohol											
Pyridine	C <sub>5</sub> H <sub>5</sub> N	TR	0,99	B	20	+	+	+	o	+	+	+	+	o	-	+	+
Pyridine	C <sub>5</sub> H <sub>5</sub> N	TR			40	+	+	+	o	+	+	+	+	-	o	+	+
Pyridine	C <sub>5</sub> H <sub>5</sub> N	TR			60	+	+	+	o	o	+	+	-	-	o	+	+
Pyrogallic Acid						See Pyrogallol											
Pyrogallol	C <sub>6</sub> H <sub>3</sub> (OH) <sub>3</sub> -1,2,3	10			20	+	+	+	+	+	+	+	+	o	+	+	+
Pyrogallol	C <sub>6</sub> H <sub>3</sub> (OH) <sub>3</sub> -1,2,3	10			40	+	+	+	+	+	+	+	+	-	+	+	+
Pyrogallol	C <sub>6</sub> H <sub>3</sub> (OH) <sub>3</sub> -1,2,3	10			60	+	+	+	+	+	+	+	+	-	+	+	+
Ricinus Oil		H	0,96		20	+	+	+	+	+	+	+	+	+	+	+	+
Ricinus Oil		H			40	+	+	+	+	+	+	+	+	+	+	+	+
Ricinus Oil		H			60	+	+	+	+	+	+	+	+	+	+	+	+
Salade Oil		H			20	+	+	+	+	+	+	+	+	+	+	+	+
Salade Oil		H			40	+	+	+	+	+	+	+	+	+	o	+	+
Salade Oil		H			60	+	+	+	o	+	+	+	+	-	+	+	+
Salmiac						See Ammonium Chloride											
Salt peter						See Potassium Nitrate											
Sea Water					20	o	+	-	+	+	+	+	+	+	+	+	+
Sea Water					40	o	+	-	+	+	+	+	+	+	o	+	+
Sea Water					60	o	+	-	+	+	+	+	+	o	+	+	+
Sel Volatile						See Ammonium Carbonate											
Silicic Acid	Si(OH) <sub>4</sub>	TR			20	+	+	-	+	+	+	+	+	-	+	+	+
Silicic Acid	Si(OH) <sub>4</sub>	TR			40	+	+	-	+	+	+	+	+	-	+	+	+
Silicic Acid	Si(OH) <sub>4</sub>	TR			60	+	+	-	+	+	+	+	+	-	+	+	+
Silicofluoric Acid						See Hydrofluosilic Acid											
Silicone Oil		TR	1,06		20	+	+	+	+	+	+	+	+	+	o	+	+
Silicone Oil		TR			40	+	+	+	+	+	+	+	+	+	o	+	+
Silicone Oil		TR			60	+	+	+	+	+	+	+	+	+	o	+	+
Silver Nitrate	AgNO <sub>3</sub>	8	1,07		20	+	+	-	+	+	+	+	+	+	+	+	+
Silver Nitrate	AgNO <sub>3</sub>	8			40	+	+	-	+	+	+	+	+	+	+	+	+
Silver Nitrate	AgNO <sub>3</sub>	8			60	+	+	-	+	+	+	+	+	+	+	+	+
Soda						See Sodium Bicarbonate											
Sodium Acetate	CH <sub>3</sub> COONa	10			20	+	+	+	+	+	+	+	+	+	+	+	+
Sodium Acetate	CH <sub>3</sub> COONa	10			40	+	+	+	+	+	+	+	+	+	+	+	+

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM	
Sodium Acetate	CH <sub>3</sub> COONa	10			60	+	+	+	+	+	+	+	+	o	+	+	+	
Sodium Benzoate	C <sub>7</sub> H <sub>5</sub> NaO <sub>2</sub>	10			20	+	+	+	+	+	+	+	+	+	+	+	+	
Sodium Benzoate	C <sub>7</sub> H <sub>5</sub> NaO <sub>2</sub>	10			40	+	+	+	+	+	+	+	+	+	+	+	+	
Sodium Benzoate	C <sub>7</sub> H <sub>5</sub> NaO <sub>2</sub>	10			60	+	+	+	+	+	+	+	+	o	+	+	+	
Sodium Benzoate	C <sub>7</sub> H <sub>5</sub> NaO <sub>2</sub>	36			20	+	+	+	+	+	+	+	+	+	+	+	+	
Sodium Benzoate	C <sub>7</sub> H <sub>5</sub> NaO <sub>2</sub>	36			40	+	+	+	+	+	+	+	+	+	+	+	+	
Sodium Benzoate	C <sub>7</sub> H <sub>5</sub> NaO <sub>2</sub>	36			60	+	+	+	+	+	+	+	+	o	+	+	+	
Sodium Benzoate	C <sub>7</sub> H <sub>5</sub> NaO <sub>2</sub>	GL			20	+	+	+	+	+	+	+	+	+	+	+	+	
Sodium Benzoate	C <sub>7</sub> H <sub>5</sub> NaO <sub>2</sub>	GL			40	+	+	+	+	+	+	+	+	+	+	+	+	
Sodium Bicarbonate	NaHCO <sub>3</sub>	10	1,07		20	+	+	+	+	+	+	+	+	+	+	+	+	
Sodium Bicarbonate	NaHCO <sub>3</sub>	10			40	+	+	+	+	+	+	+	+	+	+	+	+	
Sodium Bicarbonate	NaHCO <sub>3</sub>	10			60	+	+	+	+	+	+	+	+	+	+	+	+	
Sodium Bichromate	Na <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	10			20	+	+	+	+	+	+	+	+	+	+	+	+	
Sodium Bichromate	Na <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	10			40	+	+	+	+	+	+	+	+	+	+	+	+	
Sodium Bichromate	Na <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	10			60	+	+	+	+	+	+	+	+	o	+	+	+	
Sodium Chlorate	NaClO <sub>3</sub>	25	1,23		20	+	+	-	+	+	+	+	+	+	+	+	+	
Sodium Chlorate	NaClO <sub>3</sub>	25			40	+	+	-	+	+	+	+	+	o	+	+	+	
Sodium Chlorate	NaClO <sub>3</sub>	25			60	o	+	-	+	+	+	+	+	-	+	+	+	
Sodium Chloride	NaCl	20			20	o	+	+	+	+	+	+	+	+	+	+	+	
Sodium Chloride	NaCl	20			40	o	+	+	+	+	+	+	+	+	+	+	+	
Sodium Chloride	NaCl	20			60	o	o	o	o	+	+	+	+	o	+	+	+	
Sodium Chlorite	NaClO <sub>2</sub>	5			20	o	+	-	+	+	+	+	+	+	+	+	+	
Sodium Chlorite	NaClO <sub>2</sub>	5			40	-	o	-	+	+	+	+	+	+	+	+	+	
Sodium Chlorite	NaClO <sub>2</sub>	5			60	-	o	-	+	+	+	+	+	o	+	+	+	
Sodium Dichromate					See Sodium Bichromate													
Sodium Fluoride	NaF	4	1,04		20	+	+	-	+	+	+	+	+	+	+	+	+	+
Sodium Fluoride	NaF	4			40	+	+	-	+	+	+	+	+	o	+	+	+	+
Sodium Fluoride	NaF	4			60	o	+	-	+	+	+	+	+	o	+	+	+	+
Sodium Hydroxyde	NaOH	10	1,16		20	+	+	-	+	o	+	+	+	+	+	+	+	+
Sodium Hydroxyde	NaOH	10			40	+	+	-	+	o	+	+	+	+	+	+	+	+
Sodium Hydroxyde	NaOH	10			60	+	+	-	+	o	+	+	+	o	o	+	+	+
Sodium Hydroxyde	NaOH	30	1,33		20	+	+	-	+	o	+	+	o	+	+	+	+	+
Sodium Hydroxyde	NaOH	30			40	+	+	-	+	o	+	+	+	o	o	+	+	+
Sodium Hydroxyde	NaOH	30			60	+	+	-	+	o	+	+	+	o	o	+	+	+
Sodium Hydroxyde	NaOH	50	1,53		20	+	+	-	+	o	+	+	o	o	o	+	+	+
Sodium Hydroxyde	NaOH	50			40	+	+	-	+	o	+	+	+	o	-	+	+	+
Sodium Hydroxyde	NaOH	50			60	o	+	-	+	o	+	+	+	-	-	+	+	+
Sodium Hypochlorite	NaOCl	10			20	o	+	-	+	+	+	+	+	-	+	+	+	+
Sodium Hypochlorite	NaOCl	12,5			20	o	+	-	+	+	+	+	+	-	+	+	+	+
Sodium Hypochlorite	NaOCl	12,5			40	o	+	-	o	+	+	+	+	o	-	o	+	+
Sodium Hypochlorite	NaOCl	20			20	o	+	-	+	+	+	+	+	-	+	+	+	+
Sodium Hypochlorite	NaOCl	20			40	o	+	-	o	+	+	+	+	o	-	o	+	+
Sodium Hypochlorite	NaOCl	20			60	o	+	-	-	+	+	+	+	o	-	o	+	+
Sodium Hyposulphide					See Sodium Thiosulphate													
Sodium Nitrate	NaNO <sub>3</sub>	45	1,37		20	+	+	+	+	+	+	+	+	+	+	+	+	+
Sodium Nitrate	NaNO <sub>3</sub>	45			40	+	+	+	+	+	+	+	+	+	+	+	+	+
Sodium Nitrate	NaNO <sub>3</sub>	45			60	+	+	+	+	+	+	+	+	+	+	+	+	+
Sodium Nitrite	NaNO <sub>2</sub>	50			20	+	+	+	+	+	+	+	+	+	+	+	+	+
Sodium Nitrite	NaNO <sub>2</sub>	50			40	+	+	+	+	+	+	+	+	+	o	+	+	+
Sodium Nitrite	NaNO <sub>2</sub>	50			60	+	+	+	+	+	+	+	+	-	+	+	+	+

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM
Sodium Perchlorate	NaClO <sub>4</sub>	25	1,18		20	o + + + + <sup>1)</sup>	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Perchlorate	NaClO <sub>4</sub>	25			40	o + + + + <sup>1)</sup>	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Perchlorate	NaClO <sub>4</sub>	25			60	o + o + + <sup>1)</sup>	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Phosphate	Na <sub>3</sub> PO <sub>4</sub>	10			20	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Phosphate	Na <sub>3</sub> PO <sub>4</sub>	10			40	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Phosphate	Na <sub>3</sub> PO <sub>4</sub>	10			60	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Silicate						See Sodium Water Glass											
Sodium Sulphate	Na <sub>2</sub> SO <sub>4</sub>	50	1,46		20	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Sulphate	Na <sub>2</sub> SO <sub>4</sub>	50			40	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Sulphate	Na <sub>2</sub> SO <sub>4</sub>	50			60	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Sulphite	Na <sub>2</sub> SO <sub>3</sub>	GL	1,18		20	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Sulphite	Na <sub>2</sub> SO <sub>3</sub>	GL			40	+ + o + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ o + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Sulphite	Na <sub>2</sub> SO <sub>3</sub>	GL			60	+ + - + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Tetraborate						See Borax											
Sodium Thiosulphate	Na <sub>2</sub> S <sub>2</sub> O <sub>3</sub>	40			20	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ o + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Thiosulphate	Na <sub>2</sub> S <sub>2</sub> O <sub>3</sub>	40			40	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- o - +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Thiosulphate	Na <sub>2</sub> S <sub>2</sub> O <sub>3</sub>	40			60	+ + + + o + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- - + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Water Glass	Na <sub>2</sub> SiO <sub>3</sub>	20	1,24		20	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Water Glass	Na <sub>2</sub> SiO <sub>3</sub>	20			40	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sodium Water Glass	Na <sub>2</sub> SiO <sub>3</sub>	20			60	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Spindle Oil		TR			20	+ + + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ o + +	+ + + +	+ + + +	+ + + +	+ + + +	
Spindle Oil		TR			40	+ + + + o + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Spindle Oil		TR			60	+ + + + o + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- o o -	+ + + +	+ + + +	+ + + +	+ + + +	
Spirit of Wine						See Ethanol											
Spruce-Needle Oil						See Essential Oils											
Stannous Chloride	SnCl <sub>2</sub>	20	1,17		20	o + - + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Stannous Chloride	SnCl <sub>2</sub>	20			40	o + - + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Stannous Chloride	SnCl <sub>2</sub>	20			60	o + - + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Starch Gum						See Dextrose											
Styrene	C <sub>6</sub> H <sub>5</sub> CHCH <sub>2</sub>	TR	0,91	All	20	+ + + o o + + +	+ + o o + + +	- - + + + +	+ + o o + + +	+ + o o + + +	- - + + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Succinic Acid						See Ethane Dicarboxylic Acid											
Sulphur Chloride	S <sub>2</sub> Cl <sub>2</sub>	10			20	o + o o + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- - + + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub>	40	1,30		20	o + - + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ o + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub>	40			40	- + - + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ o + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub>	40			60	- o - o + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub>	80	1,73		20	o + - + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub>	80			40	- o - + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub>	80			60	- o - o + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- o + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub>	90	1,82		20	+ + + + - o + + +	+ + + + o + + +	- - + + + +	+ + + + o + + +	+ + + + o + + +	- - + + + +	- + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub>	90			40	o + - o + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- o + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub>	90			60	o + - o + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- o + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub>	98	1,84		20	+ + + + - o + + +	+ + + + o + + +	- - + + + +	+ + + + o + + +	+ + + + o + + +	- - + + + +	- o + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub>	98			40	o + - o + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- o + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphuric Acid	H <sub>2</sub> SO <sub>4</sub>	98			60	o + - o + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- - -	- o + +	+ + + +	+ + + +	+ + + +	
Sulphuric Ether						See Ether											
Sulphurous Acid	H <sub>2</sub> SO <sub>3</sub>	50			20	o + - + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	+ o + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphurous Acid	H <sub>2</sub> SO <sub>3</sub>	50			40	o + - + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- + + +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphurous Acid	H <sub>2</sub> SO <sub>3</sub>	50			60	- o - + + +	+ + + +	- - + + + +	+ + + +	+ + + +	- - + + + +	- o - +	+ + + +	+ + + +	+ + + +	+ + + +	
Sulphite Lye						See Calcium Bisulphite											
Sylvine						See Potassium Chloride											

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM			
Tannic Acid	C <sub>2</sub> O <sub>6</sub> H <sub>6</sub>	50			20	+ <sup>1)</sup> +	-	+ <sup>1)</sup> +	+	+	-	+	+	+	+	+				
Tannic Acid	C <sub>2</sub> O <sub>6</sub> H <sub>6</sub>	50			40	+ <sup>1)</sup> +	-	+ <sup>1)</sup> +	+	+	-	+	o	+	+	+				
Tannic Acid	C <sub>2</sub> O <sub>6</sub> H <sub>6</sub>	50			60	+ <sup>1)</sup> +	-	+ <sup>1)</sup> +	+	+	-	+	-	+	+	+				
Tanning Extracts Vegetable		H			20	+ <sup>1)</sup> +	+	+ <sup>1)</sup> +	+	+	-	+	+	+	+	+				
Tanning Extracts Vegetable		H			40	+ <sup>1)</sup> +	o	+ <sup>1)</sup> +	+	+	-	+	o	+	+	+				
Tanning Extracts Vegetable		H			60	+ <sup>1)</sup> +	-	o	+	+	-	+	-	o	+	+				
Tartaric Acid	C <sub>4</sub> H <sub>6</sub> O <sub>6</sub>	GL	1,76		20	+	+	-	+	+	+	+	+	+	+	+				
Tartaric Acid	C <sub>4</sub> H <sub>6</sub> O <sub>6</sub>	GL			40	+	+	-	+	+	+	+	+	+	+	+				
Tartaric Acid	C <sub>4</sub> H <sub>6</sub> O <sub>6</sub>	GL			60	+	+	-	+	+	+	+	o	+	+	+				
Tetrachloroethane	Cl <sub>2</sub> CH-CHCl	TR	1,60		20	+	+	-	o	+	+	+	o	-	-	+	+			
Tetrachloroethane	Cl <sub>2</sub> CH-CHCl <sub>2</sub>	TR			40	+	+	-	o	+	+	+	o	-	-	+	+			
Tetrachloroethane	Cl <sub>2</sub> CH-CHCl <sub>2</sub>	TR			60	+	+	-	-	o	+	+	o	-	-	+	+			
Tetrachloroethylene						Perchlorethylene														
Tetrachloromethane	CCl <sub>4</sub>	TR	1,59		20	+ <sup>1)</sup> +	+	+	o	+	+ <sup>1)</sup> o	+	-	o	+	+	+			
Tetrachloromethane	CCl <sub>4</sub>	TR			40	+ <sup>1)</sup> +	+	o	+	+ <sup>1)</sup> o	+	-	-	+	+	+				
Tetrachloromethane	CCl <sub>4</sub>	TR			60	+ <sup>1)</sup> +	o	-	+	+ <sup>1)</sup> o	+	-	-	+	+	+				
Tetrahydrofurane	C <sub>4</sub> H <sub>8</sub> O	TR	0,89	B	20	+ <sup>1)</sup> +	-	o	o	+	+	o	-	o	+	+				
Tetrahydrofurane	C <sub>4</sub> H <sub>8</sub> O	TR			40	+ <sup>1)</sup> +	-	-	-	+	+	o	-	-	+	+				
Tetrahydrofurane	C <sub>4</sub> H <sub>8</sub> O	TR			60	+ <sup>1)</sup> +	-	-	-	+	+	o	-	-	+	+				
Tetrahydronaphthalene						Tetraline														
Tetraline	C <sub>10</sub> H <sub>12</sub>	100	0,97	AIII	20	+	+	+	-	+	+	+	+	-	o	+	+			
Tetraline	C <sub>10</sub> H <sub>12</sub>	100			40	+	+	+	-	+	+	+	+	-	-	+	+			
Tetraline	C <sub>10</sub> H <sub>12</sub>	100			60	+	+	+	-	+	+	+	+	-	-	+	+			
Thiofuran						Thiophene														
Thionyl Chloride	SOCl <sub>2</sub>	TR	1,66		20	+	+	-	-	+	+	+	+	-	-	+	+			
Thionyl Chloride	SOCl <sub>2</sub>	TR			40	+	+	-	-	+	+	+	+	-	-	+	+			
Thionyl Chloride	SOCl <sub>2</sub>	TR			60	+	+	-	-	+	+	+	-	-	+	+	+			
Thiophene	C <sub>4</sub> H <sub>4</sub> S			AI	20	+	+	-	o	+	+	+	+	-	+	+	+			
Toluene	C <sub>7</sub> H <sub>8</sub>		0,87	AI	20	+	+	+	o	+	+	o	-	o	+	+				
Toluene	C <sub>7</sub> H <sub>8</sub>				40	+	+	+	o	+	+	+	o	-	-	+	+			
Toluene	C <sub>7</sub> H <sub>8</sub>				60	+	+	+	o	+	+	+	o	-	-	+	+			
Toothpaste		H			20	+	+	+	+	+	+	+	+	+	+	+	+			
Transformer Oil		TR			20	+	+	+	o	+	+	+	+	+	o	+	+			
Transformer Oil		TR			40	+	+	+	o	+	+	+	+	+	-	+	+			
Transformer Oil		TR			60	+	+	+	o	+	+	+	+	+	-	+	+			
Tributyl Phosphate	C <sub>12</sub> H <sub>27</sub> O <sub>4</sub> P	TR	0,98		20	+	+	o	+	+	+	+	+	-	+	+	+			
Tributyl Phosphate	C <sub>12</sub> H <sub>27</sub> O <sub>4</sub> P	TR			40	+	+	o	+	+	+	+	o	-	+	+	+			
Tributyl Phosphate	C <sub>12</sub> H <sub>27</sub> O <sub>4</sub> P	TR			60	+	+	o	+	+	+	+	-	-	+	+	+			
Trichloroacetic Acid	CCl <sub>3</sub> CO <sub>2</sub> H	50			20	o	+	-	+	+	+	+	-	-	+	+	+			
Trichloroacetic Acid	CCl <sub>3</sub> CO <sub>2</sub> H	50			40	-	+	-	+	+	+	+	-	-	o	+	+			
Trichloroacetic Acid	CCl <sub>3</sub> CO <sub>2</sub> H	50			60	-	+	-	+	o	+	+	-	-	+	+	+			
Trichloroacetic Acid	CCl <sub>3</sub> CO <sub>2</sub> H	TR	1,62		20	o	+	-	+	+	+	+	-	o	+	+	+			
Trichloroacetic Acid	CCl <sub>3</sub> CO <sub>2</sub> H	TR			40	-	+	-	o	+	+	+	-	-	o	+	+			
Trichloroacetic Acid	CCl <sub>3</sub> CO <sub>2</sub> H	TR			60	-	+	-	o	o	+	+	-	-	-	+	+			
Trichlorobenzene	C <sub>6</sub> H <sub>3</sub> Cl <sub>3</sub>				20	+ <sup>1)</sup> +	-	o	+	+	-	+	-	-	+	+	+			
Trichlorobenzene	C <sub>6</sub> H <sub>3</sub> Cl <sub>3</sub>				40	+ <sup>1)</sup> +	-	o	+	+	-	+	-	-	+	+	+			
Trichlorobenzene	C <sub>6</sub> H <sub>3</sub> Cl <sub>3</sub>				60	+ <sup>1)</sup> +	-	o	+	+	-	+	-	-	o	+	+			
Trichloroethane	C <sub>2</sub> H <sub>3</sub> Cl <sub>3</sub>	TR	1,34		20	+ <sup>1)</sup> +	-	o	+	+	o	o	-	-	+	+	+			
Trichloroethylene	C <sub>2</sub> HCl <sub>3</sub>	50			20	+	+	-	o	+	+ <sup>1)</sup>	+	o	-	o	+	+			
Trichloroethylene	C <sub>2</sub> HCl <sub>3</sub>	50			40	+	+	-	o	+	+ <sup>1)</sup>	+	o	-	-	+	+			

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEP	FFKM
Trichloroethylene	C <sub>2</sub> HCl <sub>3</sub>	50			60	+	+	-	o	+	+ <sup>1)</sup>	+	o	-	-	+	+
Trichloroethylene	C <sub>2</sub> HCl <sub>3</sub>	TR	1,47		20	+	+	-	o	+	+ <sup>1)</sup>	+	+	-	o	+	+
Trichloroethylene	C <sub>2</sub> HCl <sub>3</sub>	TR			40	+	+	-	o	+	+ <sup>1)</sup>	+	o	-	-	+	+
Trichloroethylene	C <sub>2</sub> HCl <sub>3</sub>	TR			60	+	+	-	-	+	+ <sup>1)</sup>	+	o	-	-	+	+
Trichloromethane					See Chloroform												
Trichlorophenol					See Trichlorobenzene												
Tricresyl Phosphate	PO <sub>4</sub> (C <sub>6</sub> H <sub>4</sub> CH <sub>3</sub> ) <sub>3</sub>	TR	1,13		20	+	+	+	+	+	+	+	-	o	o	+	+
Tricresyl Phosphate	PO <sub>4</sub> (C <sub>6</sub> H <sub>4</sub> CH <sub>3</sub> ) <sub>3</sub>	TR			40	+	+	+	o	+	+	+	-	-	-	+	+
Tricresyl Phosphate	PO <sub>4</sub> (C <sub>6</sub> H <sub>4</sub> CH <sub>3</sub> ) <sub>3</sub>	TR			60	+	+	+	o	+	+	+	-	-	-	+	+
Triethylamine	C <sub>6</sub> H <sub>15</sub> N	TR	0,73	B	20	+	+	+	+	o	+	+	+	-	+	+	+
Triethylamine	C <sub>6</sub> H <sub>15</sub> N	TR			40	+	+	+	+	o	+	+	+	-	+	+	+
Triiodinemethane	CHJ <sub>3</sub>				20	+	+	-	+	+	+	+	+	+	o	+	+
Triiodinemethane	CHJ <sub>3</sub>				40	+	+	-	+	+	+	+	+	+	o	+	+
Triiodinemethane	CHJ <sub>3</sub>				60	+	+	-	+	+	+	+	+	o	-	+	+
Trilene					See Trichloroethylene												
Triol					See Butane Triol												
Trisodium Phosphate					See Sodium Phosphate												
Turpentine Oil		H	0,86		20	+	+	+	-	+	+	+	+	+	-	+	+
Turpentine Oil		H			40	+	+	+	-	o	+	+	+	+	-	+	+
Turpentine Oil		H			60	+	+	+	-	o	+	+	+	+	-	+	+
Urea	CH <sub>4</sub> N <sub>2</sub> O	10			20	+	+	+	+	+	+	+	+	+	+	+	+
Urea	CH <sub>4</sub> N <sub>2</sub> O	10			40	+	+	+	+	+	+	+	+	+	+	+	+
Urea	CH <sub>4</sub> N <sub>2</sub> O	10			60	+	+	+	+	+	+	+	+	+	+	+	+
Urea	CH <sub>4</sub> N <sub>2</sub> O	33			20	+	+	+	+	+	+	+	+	+	+	+	+
Urea	CH <sub>4</sub> N <sub>2</sub> O	33			40	+	+	o	+	+	+	+	+	+	+	+	+
Urea	CH <sub>4</sub> N <sub>2</sub> O	33			60	+	+	o	+	+	+	+	+	+	+	+	+
Urine					20	+	+	-	+	+	+	+	+	+	+	+	+
Urine					40	+	+	-	+	+	+	+	+	+	+	+	+
Urine					60	+	+	-	+	+	+	+	+	+	+	+	+
Vinegar		H			20	+	+	o	+	+	+	+	+	-	o	+	+
Vinegar		H			40	+	+	o	+	+	+	+	+	-	o	+	+
Vinegar		H			60	+	+	-	+	+	+	+	+	-	o	o	+
Vinyl Acetate	C <sub>4</sub> H <sub>6</sub> O <sub>2</sub>	TR	0,93	AI	20	+	+	-	+	+	+	+	o	+	o	+	+
Vinyl Acetate	C <sub>4</sub> H <sub>6</sub> O <sub>2</sub>	TR			40	+	+	-	o	+	+	+	-	+	o	+	+
Vinyl Acetate	C <sub>4</sub> H <sub>6</sub> O <sub>2</sub>	TR			60	+	+	-	o	+	+	+	-	+	o	+	+
Vinyl Benzene					See Styrene												
Vinyl Carbinol					See Allyl Alcohol												
Vinyl Cyanide					See Acrylnitrile												
Vinyldenechloride					See Dichloroethylene 1.1												
Water	H <sub>2</sub> O		1,00		20	+	+	+	+	+	+	+	+	+	+	+	+
Water	H <sub>2</sub> O				40	+	+	+	+	+	+	+	+	+	+	+	+
Water	H <sub>2</sub> O				60	+	+	+	+	+	+	+	+	+	+	+	+
Water, distilled	H <sub>2</sub> O		1,00		20	+	+	o	+	+	+	+	+	+	+	+	+
Water, distilled	H <sub>2</sub> O				40	+	+	o	+	+	+	+	+	+	+	+	+
Water, distilled	H <sub>2</sub> O				60	+	+	o	+	+	+	+	+	+	o	+	+
White Spirit				All		+ <sup>1)</sup>	+	-	+ <sup>1)</sup>	+	+	o	+	o	-	+	+
White Vitriol					See Zinc Sulphate												
Wool Fat					See Lanolin												
Xylene	C <sub>6</sub> H <sub>4</sub> (CH <sub>3</sub> ) <sub>2</sub>	TR	0,86	All	20	+	+	+	-	+	+	+	+	-	-	+	+
Xylene	C <sub>6</sub> H <sub>4</sub> (CH <sub>3</sub> ) <sub>w</sub>	TR			40	+	+	+	-	+	+	+	o	-	-	+	+

TR = technically pure, GL = saturated solution, H = commercial composition  
+ = resistant, o = limited resistance, - = not resistant, <sup>1)</sup> Not resistant on FMC



## Resistance Chart

Description	Chemical Formula	Concentration in %	Density [kg/dm³]	Danger class (VbF)	Temperature [C°]	Stainless Steel 316 Ti	Hastelloy C	Aluminium alloy	PP	PVDF	ETFE	PPS	FKM	NBR	EPDM	PTFE/FEFP	FFKM
Xylene	C <sub>6</sub> H <sub>4</sub> (CH <sub>3</sub> ) <sub>2</sub>	TR			60	+	+	+	-	o	+	+	o	-	-	+	+
Zinc Chloride	ZnCl <sub>2</sub>	20	1,19		20	+	+	-	+	+	+	+	+	+	+	+	+
Zinc Chloride	ZnCl <sub>2</sub>	20			40	+	+	-	+	+	+	+	+	+	+	+	+
Zinc Chloride	ZnCl <sub>2</sub>	20			60	+	+	-	+	+	+	+	+	+	+	+	+
Zinc Chloride	ZnCl <sub>2</sub>	75	2,07		20	-	+	-	+	+	+	+	+	+	+	+	+
Zinc Chloride	ZnCl <sub>2</sub>	75			40	-	+	-	+	+	+	+	+	+	+	+	+
Zinc Chloride	ZnCl <sub>2</sub>	75			60	-	+	-	+	+	+	+	+	+	+	+	+
Zinc Sulphate	ZnSO <sub>4</sub>	10	1,11		20	+	+	o	+	+	+	+	+	+	+	+	+
Zinc Sulphate	ZnSO <sub>4</sub>	10			40	+	+	o	+	+	+	+	+	+	+	+	+
Zinc Sulphate	ZnSO <sub>4</sub>	10			60	+	+	o	+	+	+	+	+	o	+	+	+
Zinc Sulphate	ZnSO <sub>4</sub>	GL	1,38		20	+	+	o	+	+	+	+	+	+	+	+	+
Zinc Sulphate	ZnSO <sub>4</sub>	GL			40	+	+	o	+	+	+	+	+	+	+	+	+
Zinc Sulphate	ZnSO <sub>4</sub>	GL			60	+	+	-	+	+	+	+	+	o	+	+	+